



CERTIFICATE

CENTEXBEL TYPE TESTING | TEST REPORT N° 21.04725.01

According to report N° 21.04725.01, dated on 27/08/2021, we confirm that the below mentioned items were tested at CENTEXBEL with reference to **NF P 92-507 (2004) "Fire safety - Building - Interior fitting materials - Classification according to their reaction to fire"**.

The items show

Classification M1

When properly applied.

The evaluation of the burning behaviour is based on CENTEXBEL's evaluation scheme.

SAMPLES

1023

Various colours

Company

Ado Goldkante GmbH Co Kg
Zimmersmühlenweg 14-18
61440 OBERURSEL - GERMANY

This Certificate is valid until 27/08/2026

Centexbel | Technologiepark 7 | BE 9052 Gent | Belgium, 27/08/2021

Stijn Devaere, PhD
Director Services



Ado Goldkante GmbH Co Kg
Zimmersmühlenweg 14-18
61440 OBERURSEL
Germany

Your notice of
 19-07-2021

Your reference

Date
 27-08-2021

Analysis Report 21.04725.01

Required tests :

NF P92-507 (2004)

Sample id	Information given by the client	Date of receipt
T2116285	1023-200	19-07-2021
T2116286	1023-556	19-07-2021
T2116287	1023-999	19-07-2021



Gina Créelle
Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.
 The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.
 In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.



Reference: T2116285 - 1023-200
 T2116286 - 1023-556
 T2116287 - 1023-999

Classification of materials according to their reaction to fire - "Electric burner"

Date of ending the test 20-08-2021
 Standard used NF P92-503 (1995)
 Product standard NF P92-507 (2004)

Deviation from the standard A limited number of specimens have been tested for each sample.

Dimension of the specimens 600 mm x 180 mm x 1 mm
 Weight (g/m²)
 T2116285 165
 T2116286 171
 T2116287 176

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure

Conditioning 23°C, relative humidity 50%
 Minimum 7 days or until constant mass is achieved

T2116285

	Length		Width	
	Face A	Face B	Face A	Face B
Hole formation	yes			yes
Max. afterflame time (s)	0	-	-	0
Afterglow	no			no
Afterglow with propagation in area > 25 cm	no			no
Damaged length (cm)	18.5	-	-	17.0
Damaged width (cm) in area >45 cm	0	-	-	0
Flaming molten droplets	no			no
Non-flaming molten droplets	yes			yes
Flaming debris	no			no
Non-flaming debris	no			no

T2116286

	Length		Width	
	Face A	Face B	Face A	Face B
Hole formation		yes	yes	
Max. afterflame time (s)	-	0	0	-
Afterglow		no	no	
Afterglow with propagation in area > 25 cm		no	no	
Damaged length (cm)	-	18.0	17.5	-
Damaged width (cm) in area >45 cm	-	0	0	-
Flaming molten droplets		no	no	
Non-flaming molten droplets		yes	yes	
Flaming debris		no	no	
Non-flaming debris		no	no	

T2116287

	Length		Width	
	Face A	Face B	Face A	Face B
Hole formation	yes			yes
Max. afterflame time (s)	0	-	-	0
Afterglow	no			no
Afterglow with propagation in area > 25 cm	no			no
Damaged length (cm)	18.5	-	-	16.0
Damaged width (cm) in area >45 cm	0	-	-	0
Flaming molten droplets	no			no
Non-flaming molten droplets	yes			yes
Flaming debris	no			no
Non-flaming debris	no			no



Reference: T2116285 - 1023-200
 T2116286 - 1023-556
 T2116287 - 1023-999

Classification of materials according to their reaction to fire - "Flame persistence test"

Date of ending the test	25-08-2021
Standard used	NF P92-504 (1995)
Product standard	NF P92-507 (2004)
Deviation from the standard	A limited number of specimens have been tested for each sample.
Dimension of the specimens	460 mm x 230 mm x 1 mm
Weight (g/m ²)	
T2116285	165
T2116286	171
T2116287	176

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure

Conditioning 23°C, relative humidity 50%
 Minimum 7 days or until constant mass is achieved

Each test has been carried out with a flame application time of 5s.

T2116285

	Length		Width	
	Face A	Face B	Face A	Face B
#1	*			*
#2	*			*
#3	*			*
#4	*			*
#5	*			*
#6	*			*
#7	*			*
#8	*			*
#9	*			*
#10	*			*

Flaming debris no
 Non-flaming debris no

*: afterflame time ≤ 2 s
 > 2 s: afterflame time > 2 s and ≤ 5 s
 > 5 s: afterflame time > 5 s

T2116286

	Length		Width	
	Face A	Face B	Face A	Face B
#1		*	*	
#2		*	*	
#3		*	*	
#4		*	*	
#5		*	*	
#6		*	*	
#7		*	*	
#8		*	*	
#9		*	*	
#10		*	*	

Flaming debris no
 Non-flaming debris no

*: afterflame time ≤ 2 s
 > 2 s: afterflame time > 2 s and ≤ 5 s
 > 5 s: afterflame time > 5 s



T2116287

	Length		Width	
	Face A	Face B	Face A	Face B
#1	*			*
#2	*			*
#3	*			*
#4	*			*
#5	*			*
#6	*			*
#7	*			*
#8	*			*
#9	*			*
#10	*			*

Flaming debris no
 Non-flaming debris no

*: afterflame time ≤ 2 s
 > 2 s: afterflame time > 2 s and ≤ 5 s
 > 5 s: afterflame time > 5 s



Reference: T2116285 - 1023-200
 T2116286 - 1023-556
 T2116287 - 1023-999

Classification of materials according to their reaction to fire - "Test for melting materials"

Date of ending the test	26-08-2021
Standard used	NF P92-505 (1995)
Product standard	NF P92-507 (2004)
Deviation from the standard	A limited number of specimens have been tested for each sample.
Dimension of the specimens	70 mm x 70 mm x 1 mm
Number of layers	3
Weight (g/m ²)	
T2116285	165
T2116286	171
T2116287	173

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure

Conditioning 23°C, relative humidity 50%
 Minimum 7 days or until constant mass is achieved

T2116285

		First ignition (s)	Non-flaming debris	Flaming debris	Ignition cotton wool	Mass (g)
#1	face A	*	yes	no	no	2.5
#2	face B	*	yes	no	no	2.5
#3	face A					
#4	face B					

* no ignition

T2116286

		First ignition (s)	Non-flaming debris	Flaming debris	Ignition cotton wool	Mass (g)
#1	face A	*	yes	no	no	2.5
#2	face B	*	yes	no	no	2.5
#3	face A					
#4	face B					

* no ignition



T2116287

		First ignition (s)	Non-flaming debris	Flaming debris	Ignition cotton wool	Mass (g)
#1	face A	*	yes	no	no	2.5
#2	face B	*	yes	no	no	2.5
#3	face A					
#4	face B					

* no ignition