

For the Account of Zimmer & Rohde Germany
Zimmersmuhlenweg 14-18
61440 Oberursel
Germany

Client's Identification Solid Pulse FR

CERTIFICATE OF TESTING

TEST PERFORMED NFPA 701 Standard Methods of Fire Test for Flame Propagation of Textiles and Films 2023 – Test #1

TEST RESULTS

Specimen	Mass Initial (g)	Mass Final (g)	Mass Loss (%)	Drip Burn (s)	Afterflame (s)
1	17.3	12.5	28	0.0	0.0
2	17.4	13.5	22	0.0	0.0
3	17.3	12.2	29	0.0	0.0
4	17.4	12.1	30	0.0	0.0
5	17.3	12.0	31	0.0	0.0
6	17.4	13.4	23	0.0	0.0
7	17.4	13.5	22	0.0	0.0
8	17.5	16.2	7	0.0	0.0
9	17.3	12.1	30	0.0	0.0
10	17.4	14.1	19	0.0	0.0
Average	17.4	13.2	24	0.0	0.0

NOTES

Approximate weight (oz./sq. yd) 8.6

Standard Deviation 7.3

Mean + 3 SD 45.9

Product Configuration ☒ Single Layer ☐ Multi Layer

Material Tested Initially

Test Environment 70 ±4°F, 50 ±5% Relative Humidity

Conditioning ☒ Oven at 220°F (30 minutes) ☐ 70 ±4°F & 65 ±5%RH for 24 hours

Sampling As Received

Intended End-use Drapery

ACCEPTANCE CRITERIA

<