

## Test Report

No. 4359017

Date: 28/06/2019

Zimmer + Rhode  
 Zimmersmühlenweg 14-18  
 DE-61440 Oberursel/Frankfurt  
 Germany

The following sample(s) was (were) submitted and identified by the client as:

Original Sample ID	Sample Description	Sample Receipt Date
190497568	Article No. 10685	08/05/2019



SGS Customer No : 10083859  
 SGS Order No : 4955995  
 Test Report Version : 1  
 Buyer : -  
 Order No. : - dt. 07/05/2019  
 Country of Origin : -

Test Performing Period : 04/06/2019 – 26/06/2019  
 Test Performed : Selected test(s) as requested by applicant

**Overall Assessment** : **The tested sample meets class B1 building materials requirements of DIN 4102-1 (May 1998).**

Test Results : Please refer to the next pages

### SGS INSTITUT FRESENIUS GmbH

*This test report was electronically created and released:*

	date	name		function	department
created	28.06.2019	i. A.	Irina Neumann	Project Assistant	CRS NonFood - Softline
released	28.06.2019	i.V.	Kerstin Buchmann	Projektleiterin	CRS NonFood - Softlines

## Test report no. 4359017

Zimmer + Rhode  
Zimmersmühlenweg 14-18  
DE-61440 Oberursel/Frankfurt

SGS Order No.: 4955995  
Date: 28/06/2019  
Page 2/6

### Photo documentation



**Test report no. 4359017**

Zimmer + Rhode  
 Zimmersmühlenweg 14-18  
 DE-61440 Oberursel/Frankfurt

SGS Order No.: 4955995  
 Date: 28/06/2019  
 Page 3/6

**I. Test conducted\***

This test was conducted as per DIN 4102-15:1990 DIN 4102-16:1998 and DIN 4102-1:1998 Clause 6.2, and Classification in according to DIN 4102-1 (May 1998) Clause 6.1-Class B1 materials.

**II. Sample details**

General description	Fabric sample
Color	Black, Yellow, Gray
Density	326 g/m <sup>2</sup>
Size of sample	1000mm×190mm & 190mm×90mm

**Conditioning**

Prior to testing, the sample was conditioned at least 14 days to constant mass at a temperature of 23 ± 2 °C, and a relative humidity of 50 ± 6 %.

**III. Test results**

**1) “Brandschacht” Test according to DIN 4102-15 & 16**

Exposed surface: The front face

Results of “Brandschacht” Test (part 1)				
Line No.	Unit	Test assemblies No.		
		Lengthwise	Widthwise	
1	Specimen fixings according to DIN 4102 part 15, table	/	/	/
2	Max. flame height above lower sample edge;	cm	40	/
3	Time <sup>1)</sup>	min:s	1:07	/
	<u>Melting/burning through</u>		/	/
4	Time <sup>1)</sup>	min:s	0:05	/
	<u>Back of specimen</u>		/	/
5	Flaming/glowing, Time <sup>1)</sup>	min:s	0:07	/
6	Discolouring, Time <sup>1)</sup>	min:s	0:03	/
	<u>Burning droplets</u>		No	/
7	Begin <sup>1)</sup>	min:s	/	/
	<u>Amount</u>		/	/
8	Specimen material falling off in separate droplets		/	/
9	Specimen material falling off continuously		/	/

**Test report no. 4359017**

Zimmer + Rhode  
 Zimmersmühlenweg 14-18  
 DE-61440 Oberursel/Frankfurt

SGS Order No.: 4955995  
 Date: 28/06/2019  
 Page 4/6

Results of "Brandschacht" Test (part 2)			
Line No.	Unit	Test assemblies No.	
		Lengthwise	Widthwise
	<u>Burning parts</u>	No	/
10	Begin 1)	/	/
11	Parts of sample falling off separately	/	/
12	Parts of sample falling off continuously	/	/
13	Duration of continued combustion on mesh base (max.)	No	/
	<u>Burner flame impairment by dripping/falling material</u>	No	/
14	Time <sup>1)</sup>	/	/
	<u>Premature ending of test</u>	/	/
15	End of burning at specimen <sup>1)</sup>	/	/
16	Time when test terminated (if applicable) <sup>1)</sup>	/	/
	<u>Burning after end of test</u>	No	/
17	Duration	/	/
18	Number of specimens	/	/
19	Front of specimen	/	/
20	Back of specimen	/	/
21	Height of flame	/	/
	<u>Glowing after end of test</u>	No	/
22	Duration	/	/
23	Number of specimens	/	/
24	Front of specimen	/	/
25	Back of specimen	/	/
26	Top half of specimen	/	/
27	Bottom half of specimen	/	/

**Test report no. 4359017**

Zimmer + Rhode  
 Zimmersmühlenweg 14-18  
 DE-61440 Oberursel/Frankfurt

SGS Order No.: 4955995  
 Date: 28/06/2019  
 Page 5/6

Results of "Brandschacht" Test (part 3)					
Line No.	Unit	Test assemblies No.			
		Lengthwise		Widthwise	
28	<u>Residual length</u>	/		/	
	Single results	65	64	/	/
		67	65	/	/
29	Average of the single results	65.3		/	
	<u>Smoke temperature</u>	/		/	
30	Max. of average	°C		123.5	
31	Time <sup>1)</sup>	min:s		8:19	

Note: <sup>1)</sup> time from start of testing

\*Reduction in number of test (*DIN 4102 Part 16, clause 5.2*)

Class B1 materials:

If the residual length measured after the first test is 45cm or greater, further tests are not required.

**2) Normal Flammability Test according to DIN 4102-1 Clause 6.2**

Edge ignition

Fire application time: 15s

Parameter	1	2	3	4	5	6	7	8	9	10
Whether or not flaming extinguished before reach the gauge mark(Yes/No)	Yes	Yes	Yes	Yes	Yes	Yes	Yes	Yes	Yes	Yes
Whether or not flaming reach the measuring mark within 20 seconds (Yes/No)	No	No	No	No	No	No	No	No	No	No
Time for the flame tip to reach the gauge mark(s)	NA	NA	NA	NA	NA	NA	NA	NA	NA	NA
Afterflame time (s)	0	0	0	0	0	0	0	0	0	0
Max. flame height (cm)	4	5	5	4	5	4	4	5	4	4
Molten dripping(Yes/No)	No	No	No	No	No	No	No	No	No	No
Smoke developments (visual impression)	Slight									

Note:

NA = Not applicable

## Test report no. 4359017

Zimmer + Rhode  
Zimmersmühlenweg 14-18  
DE-61440 Oberursel/Frankfurt

SGS Order No.: 4955995  
Date: 28/06/2019  
Page 6/6

**IV. DIN 4102-1:1998 Criteria for classification**

1) All materials, except flooring, may be classed as **B1** materials if they meet the following requirements a) and b):

a) The test using the 'Brandschacht' apparatus described in DIN 4102-15 (cf. subclause 6.1.3.1) shall be deemed passed if

- The mean value for the residual length (portion of specimen that has not burned or charred; cf. subclause 9.1 of DIN 4102-16) of each specimen is at least 15 cm and no individual values are lower than 0 cm,
- The mean effluent temperature does not exceed 200 °C in any test,
- The requirement for the residual length of each specimen is met even where there is afterflame, afterglow, or smouldering.

b) Pass DIN 4102-1: 1998 sub-clause 6.2.3 Ignitability Test if

For each specimen, flaming doesn't reach the gage mark within 20s after flame application.

2) Materials may be classed as **B2** materials if they pass the ignitability test specified in DIN 4102-1: 1998 subclause 6.2.5.

For each specimen, flaming doesn't reach the gage mark (150mm marks) within 20s after flame application.

3) Combustible materials which cannot be classed as B1 or B2 materials shall be classed as **B3** materials.

**STATEMENTS:**

This declaration of conformity is only based on the result of this laboratory activity, the impact of the uncertainty of the results was not included.

This test report does not replace any mandatory certification of the product that may be required.

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test; they are not intended to be the sole criterion for assessing the potential fire and smoke hazard of the product in use.

\*\*\* End of test report \*\*\*

This document is issued by the Company subject to its General Conditions of Service ([www.sgsgroup.de/agb](http://www.sgsgroup.de/agb)). Attention is drawn to the limitations of liability, indemnification and jurisdictional issues established therein. This document is an original. If the document is submitted digitally, it is to be treated as an original within the meaning of UCP 600. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of client's instructions, if any. The Company's sole responsibility is to its client and this document does not exonerate parties to a transaction from exercising all their rights and under the transaction documents. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Note: The sample(s) to which the findings recorded herein (the "finding s") relate was (were) probably drawn and / or provided by the client or by a third party acting at the client's direction. In this case the findings constitute no warranty of the sample's representativeness of any goods and strictly relate to the sample(s). The company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted.