



# Confidential Report

**Our Ref: 23/59464E/03/22**





Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.  
Telephone: +44 (0) 113 259 1999  
Email: [info@bttg.co.uk](mailto:info@bttg.co.uk)  
: [www.bttg.co.uk](http://www.bttg.co.uk)

Date: 23 March 2022

Our Ref: 23/59464E/03/22  
Your Ref: ---

Page: 1 of 4

**Client:** Zimmer + Rohde GmbH

Zimmersmuhlenweg 14-16  
61440 Oberursel  
Germany

**Job Title:** Fire Test on One Fabric Sample

**Clients Order Ref:** --


**Date of Receipt:** 11 March 2022

**Date Test Started:** 23 March 2022

**Description of Sample:** One sample of fabric, which was referenced by the client as;  
Pepe FR, Art. Nr: 10687, Use: Upholstery

**Work Requested:** We were asked to make the following fire test:  
BS 5852: Clause 11:2006 (2011)

- \* subcontracted test, UKAS accredited
- \*\* subcontracted test, EN ISO/IEC 17025 accredited
- \*\*\* not UKAS accredited



1066

Note: This report relates only to the samples submitted and as described in the report.

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.  
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.  
BTTG™ and Shirley® are trade names of Shirley Technologies Ltd.  
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.  
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2022 Shirley Technologies Limited. All rights reserved.



Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.  
Telephone: +44 (0) 113 259 1999  
Email: [info@bttg.co.uk](mailto:info@bttg.co.uk)  
: [www.bttg.co.uk](http://www.bttg.co.uk)

Date: 23 March 2022

Our Ref: 23/59464E/03/22  
Your Ref: ---

Page: 2 of 4

Client: Zimmer + Rohde GmbH

## Testing BS 5852: Clause 11: 2006 (2011) Assessment of the ignitability of upholstered seating by Smouldering and Flaming sources – Source 5 (Crib 5)

### Pre-Treatment

The material received no pre-treatment as the fabric is stated not to be FR treated.

### Conditioning

The sample was conditioned and tested in the environments specified in Clause 10 of BS 5852: 2006 (2011).

### Testing

The material was tested according to BS 5852:2006 (2011) Methods of test for the ignitability of upholstered composites for seating by flaming sources using Source 5 (Crib 5).

The sample was tested at 20°C and 39% relative humidity (R.H.).

The sample was tested over combustion modified polyurethane foam with a density of approximately 35-36kg/m<sup>3</sup>.



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.  
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.  
BTTG™ and Shirley® are trade names of Shirley Technologies Ltd.  
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.  
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2022 Shirley Technologies Limited. All rights reserved.



Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.  
 Telephone: +44 (0) 113 259 1999  
 Email: [info@bttg.co.uk](mailto:info@bttg.co.uk)  
 : [www.bttg.co.uk](http://www.bttg.co.uk)

Date: 23 March 2022

Our Ref: 23/59464E/03/22  
 Your Ref: ---

Page: 3 of 4

Client: Zimmer + Rohde GmbH

## Results

The following test results relate only to the ignitability of the combination of upholstery composites under the particular conditions of test stated; they are not intended as a means of assessing the full potential fire hazard of the materials or products in use.

	Specimen 1	Specimen 2
Time of Ignition (s)	5	5
Time of Flame Extinction (s)	172	182
Time of Smoke Extinction (s)	474	485
Time of cover split	9	9
<b>Extent of damage (mm) - Seat</b>		
Width	153	154
Length	112	108
Depth	68	68
<b>Extent of damage (mm) - Back</b>		
Width	109	120
Length	370	353
Depth	46	58
Melting	Yes	Yes
Dripping	No	No
Charring	Yes	Yes
Comments and Observations	--	--
<b>Specimen Result (Ignition or Non-ignition)</b>	<b>Non-Ignition</b>	<b>Non-Ignition</b>

## Acronyms

ME – Manually extinguished  
 DNO – Did not observe time of events

EC – Escalating combustion  
 BTT – Burnt through thickness of foam

DNS – Material did not split  
 BTE – Burnt to extremities



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.  
 A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.  
 BTTG™ and Shirley® are trade names of Shirley Technologies Ltd.  
 The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.  
 Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2022 Shirley Technologies Limited. All rights reserved.



Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.  
Telephone: +44 (0) 113 259 1999  
Email: [info@bttg.co.uk](mailto:info@bttg.co.uk)  
: [www.bttg.co.uk](http://www.bttg.co.uk)

Date: 23 March 2022

Our Ref: 23/59464E/03/22

Your Ref: ---

Page: 4 of 4

Client: Zimmer + Rohde GmbH

## Comment

The results indicate 'Non-Ignition' of the materials and the test is designated NI/5 (ie. Pass).


An estimation of uncertainty of measurement has been taken into account when making a judgment to any pass/fail criteria. Under our Policy we have used a non-binary decision rule.

See our Decision rules Policy (<http://www.bttg.co.uk/decision-rules-policy>) for further information.

## Uncertainty Budget

Measurements:  $\pm 2$  mm

Timings:  $\pm 2$  seconds

Reported by:  B Bland, Technical Customer Services Officer

Countersigned by:  P Doherty, Manager

Enquiries concerning this report should be addressed to Customer Services.



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.  
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.  
BTTG™ and Shirley® are trade names of Shirley Technologies Ltd.  
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.  
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2022 Shirley Technologies Limited. All rights reserved.