



## Test Report

No.: SL118002579869TX

Date: Jul 10, 2018

Page 1 of 2

ZIMMER & ROHDE GMBH  
ZIMMERSMUHLENWEG  
14-18 OBERURSER  
,FRANKFURT,61440,Germany

The following sample was submitted and identified by the client as:

ONE SAMPLE OF 63% CO 22% PES 15% PAN CUTTING.

Brand	:	ZR
Application No.	:	WORLCET-RY001-KB5
Fibre Content	:	63% CO 22% PES 15% PAN
Style No.	:	10790
Item No.	:	10790
Fabric Width	:	140 cm
Country Of Origin	:	Italy
Country Of Destination	:	Worldwide
Sample Receiving Date	:	Jul 03, 2018
Test Performing Period	:	Jul 04, 2018 – Jul 10, 2018
Test Performed	:	Selected test(s) as requested by applicant (details please refer to result page(s)).
	*	* * *
Test Results	:	Please refer to the next page(s).

Signed for and on behalf of  
SGS Hong Kong Ltd.

Poon Wai Man, Lolita  
Assistant Technical Manager

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.





## Test Report

No.: SL118002579869TX

Date: Jul 10, 2018

Page 2 of 2

### Test Results :

#### Abrasion Resistance

(ISO 12947-2-2016; Martindale Wear & Abrasion Tester ; 9 kPa Pressure)

End point (rubs)

65000

Specified  
Requirement  
Min. 100,000  
rubs

\*\*\* End of Report \*\*\*

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.