



Date of Issue: 2/15/2024 Report Number: 24-000304

Revision Number:1

Date Order Received: 02/12/2024

For the Account of: Zimmer & Rohde Germany Zimmersmuhlenweg 14-18

61440 Oberursel

Germany

Client's	Identification:
CIICIILO	iu c niincanon.

10839

CERTIFICATE OF TESTING

TEST PERFORMED: NFPA 260 Standard Methods of Tests and Classification System for Cigarette Ignition Resistance of Components of Upholstered Furniture – 2013; Fabric Cover Test and UFAC Fabric Classification Test Method – 1990; Standard Test Methods for Cigarette Ignition Resistance of Components of Upholstered Furniture ASTM E 1353-16 - Cover **Fabric Test**

TEST RESULTS

Specimen	Char Length (in
1	0.5
2	0.6
3	0.6

NOTES

Test Conditions: 70 ±4°F, 65 ±5% Relative Humidity

ACCEPTANCE CRITERIA

- 1. If the test specimen has no ignition, or if no individual specimen yields a vertical char of 45 mm (1.75 in; ASTM states 1.8 in.) or less, the fabric is classified a Class I cover fabric.
- If the vertical char of the test specimen greater than 45 mm (1.75 in.; ASTM states 1.8 in), the fabric is classified a Class II cover
- If an obvious ignition of the polyurethane substrate occurs on the test assembly, the fabric is classified a Class II cover fabric.

CONCLUSION	Based on the above Results and Acceptance Criteria, the item tested is:	
	☑ Class I	
	☐ Class II	

CERTIFICATION I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

Berta Stiven

Date Order Completed: 02/15/2024 Authorized Signature