



Zimmer + Rohde GmbH
Zimmersmühlenweg 14-18
61440 OBERURSEL
Deutschland

Your notice of
12-11-2025

Your reference
5508651

Date
13-01-2026

Analysis Report 25.06150.01


Required tests :

IMO - 2010 FTP Code Annex 1 - Fire test procedures - Part 8 **Fire tests - Test for upholstered furniture - smouldering cigarette test**
IMO - 2010 FTP Code Annex 1 - Fire test procedures - Part 8 **Fire tests - Test for upholstered furniture - Match flame equivalent**

Sample id	Information given by the client	Date of receipt
T2523368	Article 10913 Splendid Mohair - Composition: Grund 100%CO, Flor 100%WM	12-11-2025

Petra Wittevrongel
Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.
The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.
In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.



**Reference: T2523368 - Article 10913 Splendid Mohair - Composition: Grund
100%CO, Flor 100%WM**

IMO upholstered furniture


Information given by the client

Type of furniture

Upholstery

Fabric


Composition	100% mohair pile / 100% cotton back
Structure	Velvet
Number of threads - warp	-
Number of threads - weft	-
Yarn count - warp	-
Yarn count - weft	-
Thickness in mm	-
Weight g/m ²	805
Colour	-
Fire retardant treatment	No



**Reference: T2523368 - Article 10913 Splendid Mohair - Composition: Grund
 100%CO, Flor 100%WM**

Fire tests - Test for upholstered furniture - smouldering cigarette test

Date of ending the test	08-01-2026
Standard used	IMO - 2010 FTP Code Annex 1 - Fire test procedures - Part 8
Deviation from the standard	-
Conditioning	23°C, relative humidity 50%
Filling	T 23140 (Euro-mousse) * - non-fire retardant foam - ± 22 kg/m ³ * standard non-FR PU-foam (as indicated in Appendix 2 and 3 of Part 8)
Dimension of the specimens	800 mm x 650 mm x 5 mm
Weight (g/m ²)	811
Ignition source: smouldering cigarette with the following specifications	
Length: (70 ± 4) mm	
Diameter: (8.0 ± 0.5) mm	
Mass: (0.95 ± 0.15) g	
Smouldering rate: (11.0 ± 4.0) min / 50 mm	



	1	2
Smouldering criteria		
Unsafe escalating combustion	no	no
Test assembly consumed	no	no
Smoulders to extremities	no	no
Smoulders through thickness	no	no
Smoulders more than 1 hour	no	no
Final examination / active smouldering	no	no
Flaming criteria		
Occurrence of flames	no	no
Additional observations		
Maximum extent of damage from the ignition source (mm)	5	5
	non-ignition	non-ignition

Conclusion Pass


The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test: they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.



**Reference: T2523368 - Article 10913 Splendid Mohair - Composition: Grund
100%CO, Flor 100%WM**

Fire tests - Test for upholstered furniture - Match flame equivalent

Date of ending the test	08-01-2026
Standard used	IMO - 2010 FTP Code Annex 1 - Fire test procedures - Part 8
Deviation from the standard	-
Conditioning	23°C, relative humidity 50%
Filling	T 23140 (Euro-mousse) * - non-fire retardant foam - ± 22 kg/m ³ * standard non-FR PU-foam (as indicated in Appendix 2 and 3 of Part 8)
Dimension of the specimens	800 mm x 650 mm x 5 mm
Weight (g/m ²)	811
Flame application time (s)	20



	1	2
Smouldering criteria		
Unsafe escalating combustion	no	no
Test assembly consumed	no	no
Smoke/heat/glowing more than 120 s	no	no
Final examination / active smouldering	no	no
Flaming criteria		
Unsafe escalating combustion	no	no
Test assembly consumed	no	no
Flaming > 120 s	no	no
Afterflame time (s)	0	0
Additional observations		
Afterglow time (s)	0	0
Maximum extent of damage from the ignition source (mm)	50	40
	non-ignition	non-ignition

Conclusion Pass

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test: they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.