



Confidential Report

Our Ref: 23/59821A/06/22





Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
Telephone: +44 (0) 113 259 1999
Email: onestopshop@bttg.co.uk
Website: www.bttg.co.uk

Date: 20 June 2022

Our Ref: 23/59821A/06/22
Your Ref: ---

Page: 1 of 4

Client: Zimmer + Rohde GmbH

Zimmersmuhlenweg 14-18
61440 Oberursel
Frankfurt
Germany

Job Title: Fire Test on One Fabric Sample

Clients Order Ref: ---

Date of Receipt: 13 June 2022

Date Test Started: 20 June 2022

Description of Sample: One sample of fabric, which was referenced by the client as;
10940 - 100% PES FR

Work Requested: We were asked to make the following fire test:
BS 5867: Part 2:Type B:2008 (2015), Before and After Water Soaking

- * subcontracted test, UKAS accredited
- ** subcontracted test, EN ISO/IEC 17025 accredited
- *** not UKAS accredited



1066

Note: This report relates only to the items tested.

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.
BTTG™ and Shirley® are trade names of Shirley Technologies Ltd.
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2022 Shirley Technologies Limited. All rights reserved.



Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
Telephone: +44 (0) 113 259 1999
Email: onestopshop@bttg.co.uk
Website: www.bttg.co.uk

Date: 20 June 2022

Our Ref: 23/59821A/06/22
Your Ref: ---

Page: 2 of 4

Client: Zimmer + Rohde GmbH

BS 5867: Part 2: 2008 (2015): Type B Curtains, Drapes and Blinds

Conditioning

The test specimens were conditioned for at least 24 hours in the standard atmosphere of 65 ± 5 % relative humidity and 20 ± 2 °C.

Testing as received

Three specimens from both length and width were tested in accordance with BS EN ISO 15025:Procedure A (surface ignition):2002. The sample was tested at 17°C and 50% relative humidity.

Each specimen was subjected to an applied flame using propane and a 15 second flame application time. The results obtained (shown in the table below) were assessed according to the requirements of BS 5867:Part 2:Type B:2008 (2015).

Pre-treatment

If the fabric is a pass in the `as received` condition then the fabric is subjected a water soak and drying procedure as specified in BS EN 1021-1 & 2:Annex D:2006.

Testing after pre-treatment

Three specimens, after pre-treatment, from both length and width were tested following the procedure described above.



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.
BTTG™ and Shirley® are trade names of Shirley Technologies Ltd.
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2022 Shirley Technologies Limited. All rights reserved.



Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
 Telephone: +44 (0) 113 259 1999
 Email: onestopshop@bttg.co.uk
 Website: www.bttg.co.uk

Date: 20 June 2022

Our Ref: 23/59821A/06/22
 Your Ref: ---

Page: 3 of 4

Client: Zimmer + Rohde GmbH

Results - Testing as Received:

Specimen No.	Length			Width		
	1	2	3	4	5	6
Flame reached an edge	No	No	No	No	No	No
Hole reached an edge	No	No	No	No	No	No
Flaming debris separated	No	No	No	No	No	No
Afterflame (s)	0	0	0	0	0	0
Afterglow (s)	0	0	0	0	0	0

Requirements - Any "Yes" means fail except if only one specimen fails a further 6 specimens are tested, if the second 6 specimens all pass the result is a pass.

Result in 'as received': Pass

Results - Testing after pre-treatment:

Specimen No.	Length			Width		
	1	2	3	4	5	6
Flame reached an edge	No	No	No	No	No	No
Hole reached an edge	No	No	No	No	No	No
Flaming debris separated	No	No	No	No	No	No
Afterflame (s)	0	0	0	0	0	0
Afterglow (s)	0	0	0	0	0	0

Requirements - Any "Yes" means fail except if only one specimen fails a further 6 specimens are tested, if the second 6 specimens all pass the result is a pass.

Result in 'after pre-treatment': Pass





Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
Telephone: +44 (0) 113 259 1999
Email: onestopshop@bttg.co.uk
Website: www.bttg.co.uk

Date: 20 June 2022

Our Ref: 23/59821A/06/22

Your Ref: ---

Page: 4 of 4

Client: Zimmer + Rohde GmbH

Comment

The fabric meets the Type B performance requirements of BS 5867: Part 2: Type B:2008 (2015).

This material should be identified with the manufacturers name, trademark or other identifying mark, the statement 'Flammability complies with the requirements of BS 5867: Part 2:Type B and instructions of any special precautions to be taken concerning care (including cleansing) of the curtain, drape or window blind to be manufactured from the fabric, preferably using an appropriate care labelling symbol in accordance with BS EN 23758 and taking account of the pre-treatment using in this test and the requirements of Clause 4 of BS 5867:Part 2:2008 (2015). If the fabric is unsuitable for cleansing, this shall be stated.

Where required to make a judgement to any pass/fail criteria an estimation of uncertainty of measurement has been taken into account. Under our Policy we have used a non-binary decision rule.

See our decision rules Policy (<http://www.bttg.co.uk/decision-rules-policy>) for further information.

Uncertainty Budget

Measurements are not taken and pass/fail is related to flame extremities and flaming debris, as such any risk of false acceptance/false rejection is inherent with this standard and would be outside of 95% probability in any case. As such UoM is Zero providing all input parameters are correct.

There is no uncertainty budget associated with BS 5867:Part 2:Type B as no measurements are determined , the pass/fail criteria is assessed visually.

Reported by:.......... B Bland, Technical Customer Services Officer

Countersigned by:.......... P Doherty, Manager

Enquiries concerning this report should be addressed to Customer Services.



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.
BTTG™ and Shirley® are trade names of Shirley Technologies Ltd.
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2022 Shirley Technologies Limited. All rights reserved.