



CERTIFICATE

CENTEXBEL TYPE TESTING | TEST REPORT N° 22.02681.01

According to report N° 22.02681.01, dated on 31/05/2022, we confirm that the below mentioned items were tested at CENTEXBEL with reference to **NF P 92-507 (2004) "Fire safety - Building - Interior fitting materials - Classification according to their reaction to fire"**.

The items show

Classification M1

When properly applied.

The evaluation of the burning behaviour is based on CENTEXBEL's evaluation scheme.

SAMPLES

10940

Various colours

Company

Zimmer + Rohde GmbH

Zimmersmühlenweg 14-18

61440 OBERURSEL - GERMANY

This Certificate is valid until 31/05/2027

Centexbel | Technologiepark 70 | BE 9052 Gent | Belgium, 31/05/2022

Stijn Devaere, PhD
Director Services



Zimmer & Rohde GmbH
Zimmersmühlenweg 14 18
61440 OBERURSEL
Germany

Your notice of
 12-05-2022

Your reference

Date
 31-05-2022

Analysis Report 22.02681.01

Required tests :

NF P92-507 (2004)

Sample id	Information given by the client	Date of receipt
T2209882	10940 - col. 900	12-05-2022
T2209883	10940 - col. 998	12-05-2022
T2209884	10940 - col. 387	12-05-2022

Gina Créelle
Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.
 The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.
 In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.



Reference: T2209882 - 10940 - col. 900
T2209883 - 10940 - col. 998
T2209884 - 10940 - col. 387

Classification of materials according to their reaction to fire - "Electric burner"

Date of ending the test 24-05-2022
Standard used NF P92-503 (1995)
Product standard NF P92-507 (2004)

Deviation from the standard A limited number of specimens have been tested for each sample.

Dimension of the specimens 600 mm x 180 mm x 1 mm
Weight (g/m²) T2209882: 213
T2209883: 213
T2209884: 202

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure

Conditioning 23°C, relative humidity 50%
Minimum 7 days or until constant mass is achieved

T2209882

	Length		Width	
	Face A	Face B	Face A	Face B
Hole formation	yes			yes
Max. afterflame time (s)	0	-	-	0
Afterglow	no			no
Afterglow with propagation in area > 25 cm	no			no
Damaged length (cm)	14.0	-	-	14.0
Damaged width (cm) in area >45 cm	0	-	-	0
Flaming molten droplets	no			no
Non-flaming molten droplets	no			no
Flaming debris	no			no
Non-flaming debris	no			no

T2209883

	Length		Width	
	Face A	Face B	Face A	Face B
Hole formation		yes	yes	
Max. afterflame time (s)	-	0	0	-
Afterglow		no	no	
Afterglow with propagation in area > 25 cm		no	no	
Damaged length (cm)	-	15.0	14.0	-
Damaged width (cm) in area >45 cm	-	0	0	-
Flaming molten droplets		no	no	
Non-flaming molten droplets		no	yes	
Flaming debris		no	no	
Non-flaming debris		no	no	

T2209884

	Length		Width	
	Face A	Face B	Face A	Face B
Hole formation	yes			yes
Max. afterflame time (s)	0	-	-	0
Afterglow	no			no
Afterglow with propagation in area > 25 cm	no			no
Damaged length (cm)	14.5	-	-	14.5
Damaged width (cm) in area >45 cm	0	-	-	0
Flaming molten droplets	no			no
Non-flaming molten droplets	no			no
Flaming debris	no			no
Non-flaming debris	no			no



Reference: T2209882 - 10940 - col. 900
T2209883 - 10940 - col. 998
T2209884 - 10940 - col. 387

Classification of materials according to their reaction to fire - "Flame persistence test"

Date of ending the test	24-05-2022
Standard used	NF P92-504 (1995)
Product standard	NF P92-507 (2004)
Deviation from the standard	A limited number of specimens have been tested for each sample.
Dimension of the specimens	460 mm x 230 mm x 1 mm
Weight (g/m ²)	T2209882: 213 T2209883: 213 T2209884: 202
The test specimens have not been cleaned nor submitted to an accelerated ageing procedure	
Conditioning	23°C, relative humidity 50% Minimum 7 days or until constant mass is achieved
Each test has been carried out with a flame application time of 5s.	

T2209882

	Length		Width	
	Face A	Face B	Face A	Face B
#1	*			*
#2	*			*
#3	*			*
#4	*			*
#5	*			*
#6	*			*
#7	*			*
#8	*			*
#9	*			*
#10	*			*

Flaming debris no

Non-flaming debris no

*: afterflame time ≤ 2 s

> 2 s: afterflame time > 2 s and ≤ 5 s

> 5 s: afterflame time > 5 s

T2209883

	Length		Width	
	Face A	Face B	Face A	Face B
#1		*	*	
#2		*	*	
#3		*	*	
#4		*	*	
#5		*	*	
#6		*	*	
#7		*	*	
#8		*	*	
#9		*	*	
#10		*	*	

Flaming debris no

Non-flaming debris no

*: afterflame time ≤ 2 s

> 2 s: afterflame time > 2 s and ≤ 5 s

> 5 s: afterflame time > 5 s

T2209884

	Length		Width	
	Face A	Face B	Face A	Face B
#1	*			*
#2	*			*
#3	*			*
#4	*			*
#5	*			*
#6	*			*
#7	*			*
#8	*			*
#9	*			*
#10	*			*

Flaming debris no

Non-flaming debris no

*: afterflame time ≤ 2 s

> 2 s: afterflame time > 2 s and ≤ 5 s

> 5 s: afterflame time > 5 s



Reference: T2209882 - 10940 - col. 900
T2209883 - 10940 - col. 998
T2209884 - 10940 - col. 387

Classification of materials according to their reaction to fire - "Test for melting materials"

Date of ending the test	31-05-2022
Standard used	NF P92-505 (1995)
Product standard	NF P92-507 (2004)
Deviation from the standard	A limited number of specimens have been tested for each sample.
Dimension of the specimens	70 mm x 70 mm x 2 mm
Number of layers	2
Weight (g/m ²)	T2209882: 213 T2209883: 213 T2209884: 202

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure

Conditioning 23°C, relative humidity 50%
Minimum 7 days or until constant mass is achieved



T2209882

		First ignition (s)	Non-flaming debris	Flaming debris	Ignition cotton wool	Mass (g)
#1	face A	*	yes	no	no	2.3
#2	face B	*	yes	no	no	2.3
#3						
#4						

* no ignition

T2209883

		First ignition (s)	Non-flaming debris	Flaming debris	Ignition cotton wool	Mass (g)
#1	face A	*	yes	no	no	2.3
#2	face B	*	yes	no	no	2.3
#3						
#4						

* no ignition

T2209884

		First ignition (s)	Non-flaming debris	Flaming debris	Ignition cotton wool	Mass (g)
#1	face A	*	yes	no	no	2.2
#2	face B	*	yes	no	no	2.3
#3						
#4						

* no ignition