

RAPPORTO DI PROVA N°:
Test Report N°.

006732/25

DITTA PRESENTATRICE:
Applicant:

DESCRIZIONE CAMPIONE (fornita dal cliente):
Sample description (made by customer) :

Sample of knitted fabric colour white named **STYLE VERBIER
LIGHT B.**

CAMPIONAMENTO:
Sampling:


A cura del cliente
Made by the customer

DATA RICEVIMENTO:
Date of Receipt:

28 marzo 2025
March 28, 2025

DATA ESECUZIONE PROVE:
Test execution date:

Dalla data di ricevimento alla data di emissione
From the date of receipt to the date of issue



RISULTATI DI LABORATORIO

TEST RESULTS

Le prove non accreditate Accredia sono quelle indicate con l'asterisco *

I risultati enunciati si riferiscono unicamente ai campioni così come ricevuti, se non diversamente indicato nel rapporto di prova, e non alla partita che gli stessi rappresentano. I campioni analizzati si conservano per tre mesi. Il presente rapporto di prova ha valore solo se in originale e non può essere riprodotto parzialmente, salvo approvazione scritta del laboratorio

Test that are marked with an asterisk * are not accredited by Accredia

The declared results refer only to the samples as received, if not otherwise specified in the test report, and not to the batch they represent. The analysed samples will be kept for three months. This test report is valid only in its original form and cannot be partially reproduced without written approval of the laboratory

Italy Headquarters

BRACHI TESTING SERVICES srl
Via Sabadell, 162/21 - 59100 Prato - Italy
ph. +39.0574.591343 - fax +39.0574.593975
www.brachi.it



LAB N. 0224 L


Pag. 1 di 2

CR1-IT-01/24

RAPPORTO DI PROVA N° - TEST REPORT N° : 006732/25

TEXTILE-DETERMINATION OF THE ABRASION RESISTANCE OF FABRICS BY THE MARTINDALE METHOD	
Test Method	ISO 12947-1:1998/COR1:2002 + ISO 12947-2:2016
Test carried out under normal atmosphere at	20°C +/- 2°C ; 65% +/- 4% U.R.
Testing Apparatus	Martindale J.H.HEALS
Pressure:	12 kPa
Specimen	Pile fabric with knitted fabric base
Specimen preparatory treatment	-
Departure from the procedure	-
RESULTS	
SPECIMEN 1 - Revs	50000
SPECIMEN 2 - Revs	50000
SPECIMEN 3 - Revs	50000
Beginning loss of pile at 8000 revs	
Total uncovering of the interlacing at 20000 revs	
No breaks of threads at 50000 revs	
Presence of Pilling	No
Removed Pilling	No

Prato, 02 aprile 2025



P.I. Primo Brachi
Direttore



La copia originale del certificato può essere scaricata dal sito <http://mylab.brachi.it/validaterdp.aspx> usando il seguente codice: ocWZq0RSynCplekKXlyICA==

FINE DEL RAPPORTO DI PROVA

END OF TEST REPORT

Le prove non accreditate Accredia sono quelle indicate con l'asterisco *

I risultati enunciati si riferiscono unicamente ai campioni così come ricevuti, se non diversamente indicato nel rapporto di prova, e non alla partita che gli stessi rappresentano. I campioni analizzati si conservano per tre mesi. Il presente rapporto di prova ha valore solo se in originale e non può essere riprodotto parzialmente, salvo approvazione scritta del laboratorio

Test that are marked with an asterisk * are not accredited by Accredia

The declared results refer only to the samples as received, if not otherwise specified in the test report, and not to the batch they represent. The analysed samples will be kept for three months. This test report is valid only in its original form and cannot be partially reproduced without written approval of the laboratory

Italy Headquarters

BRACHI TESTING SERVICES srl
Via Sabadell, 162/21 - 59100 Prato - Italy
ph. +39.0574.591343 - fax +39.0574.593975
www.brachi.it



LAB N. 0224 L

Pag. 2 di 2

CE1-IT-01/24