



**Zimmer + Rohde GmbH**  
**Zimmersmühlenweg 14-18**  
**61440 OBERURSEL**  
**Deutschland**

**Your notice of**  
 09-07-2025

**Your reference**  
 5475353

**Date**  
 26-08-2025

## Analysis Report 25.03785.03

Required tests :

**NF P92-507 (2004)**

Sample id	Information given by the client	Date of receipt
T2513882	11034-900	09-07-2025
T2513883	11034-999	09-07-2025
T2513884	11034-125	09-07-2025



**Gina Créelle**  
**Order responsible**

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.  
 The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.  
 In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.

## Samples

T2513882  
 11034-900



T2513883  
 11034-999



T2513884  
 11034-125





**Reference:** T2513882 - 11034-900  
 T2513883 - 11034-999  
 T2513884 - 11034-125

**Classification of materials according to their reaction to fire - "Electric burner"**

Date of ending the test 21-08-2025  
 Standard used NF P92-503 (1995)  
 Product standard NF P92-507 (2004)

Deviation from the standard A limited number of specimens have been tested for each sample.

Dimension of the specimens 600 mm x 180 mm x < 1 mm  
 Weight (g/m<sup>2</sup>)  
 T2513882: 69  
 T2513883: 73  
 T2513884: 69

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure

Conditioning 23°C, relative humidity 50%  
 Minimum 7 days or until constant mass is achieved

T2513882

	Length		Width	
	Front	Back	Front	Back
Hole formation	yes			yes
Max. afterflame time (s)	0	-	-	0
Afterglow	no			no
Afterglow with propagation in area > 25 cm	no			no
Damaged length (cm)	24.0	-	-	24.0
Damaged width (cm) in area >45 cm	0	-	-	0
Flaming molten droplets	no			no
Non-flaming molten droplets	no			no
Flaming debris	no			no
Non-flaming debris	no			no

### T2513883

	Length		Width	
	Front	Back	Front	Back
Hole formation		yes	yes	
Max. afterflame time (s)	-	0	0	-
Afterglow		no	no	
Afterglow with propagation in area > 25 cm		no	no	
Damaged length (cm)	-	22.0	28.5	-
Damaged width (cm) in area >45 cm	-	0	0	-
Flaming molten droplets		no	no	
Non-flaming molten droplets		no	no	
Flaming debris		no	no	
Non-flaming debris		no	no	

### T2513884

	Length		Width	
	Front	Back	Front	Back
Hole formation	yes			yes
Max. afterflame time (s)	0	-	-	0
Afterglow	no			no
Afterglow with propagation in area > 25 cm	no			no
Damaged length (cm)	22.5	-	-	23.0
Damaged width (cm) in area >45 cm	0	-	-	0
Flaming molten droplets	no			no
Non-flaming molten droplets	no			no
Flaming debris	no			no
Non-flaming debris	no			no



**Reference:** T2513882 - 11034-900  
 T2513883 - 11034-999  
 T2513884 - 11034-125

**Classification of materials according to their reaction to fire - "Flame persistence test"**

Date of ending the test	22-08-2025
Standard used	NF P92-504 (1995)
Product standard	NF P92-507 (2004)
Deviation from the standard	A limited number of specimens have been tested for each sample.
Dimension of the specimens	460 mm x 230 mm x < 1 mm
Weight (g/m <sup>2</sup> )	T2513882: 69 T2513883: 73 T2513884: 69

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure

Conditioning 23°C, relative humidity 50%  
 Minimum 7 days or until constant mass is achieved

Each test has been carried out with a flame application time of 5s.

### T2513882

	Length		Width	
	Front	Back	Front	Back
#1	*			*
#2	*			*
#3	*			*
#4	*			*
#5	*			*
#6	*			*
#7	*			*
#8	*			*
#9	*			*
#10	*			*

Flaming debris no  
 Non-flaming debris no

\*: afterflame time  $\leq 2$  s  
 > 2 s: afterflame time > 2 s and  $\leq 5$  s  
 > 5 s: afterflame time > 5 s

### T2513883

	Length		Width	
	Front	Back	Front	Back
#1		*	*	
#2		*	*	
#3		*	*	
#4		*	*	
#5		*	*	
#6		*	*	
#7		*	*	
#8		*	*	
#9		*	*	
#10		*	*	

Flaming debris no  
 Non-flaming debris no

\*: afterflame time  $\leq 2$  s  
 > 2 s: afterflame time > 2 s and  $\leq 5$  s  
 > 5 s: afterflame time > 5 s

	Length		Width	
	Front	Back	Front	Back
#1	*			*
#2	*			*
#3	*			*
#4	*			*
#5	*			*
#6	*			*
#7	*			*
#8	*			*
#9	*			*
#10	*			*

Non-flaming debris	no
--------------------	----

> 2 s: afterflame time > 2 s and  $\leq 5$  s

> 5 s: afterflame time > 5 s



**Reference:** T2513882 - 11034-900  
 T2513883 - 11034-999  
 T2513884 - 11034-125

**Classification of materials according to their reaction to fire - "Test for melting materials"**

Date of ending the test 22-08-2025  
 Standard used NF P92-505 (1995)  
 Product standard NF P92-507 (2004)

Deviation from the standard A limited number of specimens have been tested for each sample.

Dimension of the specimens 70 mm x 70 mm x 2 mm  
 Number of layers  
 T2513882: 6  
 T2513883: 5  
 T2513884: 6

Weight (g/m<sup>2</sup>)  
 T2513882: 69  
 T2513883: 73  
 T2513884: 69

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure

Conditioning 23°C, relative humidity 50%  
 Minimum 7 days or until constant mass is achieved

T2513882

		First ignition (s)	Non-flaming debris	Flaming debris	Ignition cotton wool	Mass (g)
#1	front	*	yes	no	no	2.3
#2	back	*	yes	no	no	2.3
#3						
#4						

\* no ignition





### T2513883

		First ignition (s)	Non-flaming debris	Flaming debris	Ignition cotton wool	Mass (g)
#1	front	*	yes	no	no	2.0
#2	back	104	yes	no	no	2.0
#3						
#4						

\* no ignition

### T2513884

		First ignition (s)	Non-flaming debris	Flaming debris	Ignition cotton wool	Mass (g)
#1	front	*	yes	no	no	2.2
#2	back	*	yes	no	no	2.3
#3						
#4						

\* no ignition