

For the Account of: Zimmer & Rohde Germany
Zimmersmuhlenweg 14-18
61440 Oberursel
Germany

Client's Identification: SNOOZE FR

CERTIFICATE OF TESTING

TEST PERFORMED: NFPA 701 Standard Methods of Fire Test for Flame Propagation of Textiles and Films 2023 – Test #1

TEST RESULTS

Specimen	Mass Initial (g)	Mass Final (g)	Mass Loss (%)	Drip Burn (s)	Afterflame (s)
1	32.5	29.0	11	0.0	0.0
2	32.7	31.0	5	2.0	0.0
3	32.9	32.2	2	0.0	0.0
4	32.6	29.8	9	0.0	0.0
5	32.9	28.9	12	1.0	0.0
6	32.8	30.0	9	1.0	0.0
7	33.1	31.5	5	0.0	0.0
8	33.0	30.6	7	0.0	0.0
9	33.1	29.4	11	1.0	0.0
10	32.8	30.7	6	0.0	0.0
Average	32.8	30.3	8	0.5	0.0

NOTES

Approximate weight (oz./sq. yd): 16.1

Standard Deviation: 3.2

Mean + 3 SD: 17.6

Product Configuration: ☒ Single Layer ☐ Multi Layer
Material Tested: Initially
Test Environment: 70 ±4°F, 50 ±5% Relative Humidity
Conditioning: ☒ Oven at 220°F (30 minutes) ☐ 70 ±4°F & 65 ±5%RH for 24 hours
Sampling: As Received
Intended End-use: Drapery

ACCEPTANCE CRITERIA

Afterflame is required to be recorded; however, it is not factored into the Acceptance Criteria

1. Drip burn (Flaming Drip) shall not exceed an average of 2 seconds per specimen for the sample of 10 specimens
2. Mass Loss shall not exceed 40% for the average of 10 specimens
3. Individual specimen mass loss shall not exceeds mean + 3 SD

CONCLUSION Based on the above Results and Acceptance Criteria, the item tested:

- ☒ Complies
☐ Does Not Comply
☐ Testing of 10 additional specimens is required

CERTIFICATION I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.



Authorized Signature

Date Order Completed: 11/07/2025