

Zimmer + Rohde GmbH
Zimmersmühlenweg 14-18
61440 OBERURSEL
Germany

Your notice of
26-07-2024

Your reference

Date
03-09-2024

Analysis Report 24.04100.01

Required tests :

EN 13773 (2003)

Sample id	Information given by the client	Date of receipt
T2415280	1308	26-07-2024

Gina Créelle
Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.
The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.
In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.

Reference: T2415280 - 1308

Textiles – Burning behaviour – Curtains and drapes - Textile fabrics - Determination of the ignitability of vertically oriented specimens.

Date of ending the test	02-09-2024
Standard used	EN 1101 (1995) + A1 (2005)
Product standard	EN 13773 (2003)
Deviation from the standard	-
Conditioning	20°C, relative humidity 65%
Testing atmosphere	22°C, relative humidity 54%
Dimension of the specimens	200 mm x 80 mm
Ignition	Bottom edge


The test specimens have not been cleaned nor submitted to an accelerated ageing procedure.



Length

Flame application time (s)	Cases of ignition	Cases of non-ignition
1	0	1
2	0	1
3	0	1
4	0	1
5	0	1
6	0	1
7	0	1
8	0	1
9	0	1
10	0	1
11	0	1
12	0	1
13	0	1
14	0	1
15	0	1
16	0	1
17	0	1
18	0	1
19	0	2
20	1	5

The mean of the recorded times at which ignition was observed is calculated
 The test requires at least five instances of ignition and five instances of non-ignition.
 Because less than 5 instances of ignition have been measured, and taking into account §12 of ISO 6940, a ‘non-ignition’ for this test is recorded



Width

Flame application time (s)	Cases of ignition	Cases of non-ignition
1	0	1
2	0	1
3	0	1
4	0	1
5	0	1
10	0	1
15	0	1
20	0	5

The mean of the recorded times at which ignition was observed is calculated
 No ignition within 20 s

Minimum ignition time

The test requires at least five instances of ignition and five instances of non-ignition.
 Because less than 5 instances of ignition have been measured, and taking into account §12 of ISO 6940, a 'non-ignition' for this test is recorded

Reference: T2415280 - 1308

Textiles and textile products – Burning behaviour – Curtains and drapes. Measurement of flame spread of vertically oriented specimens with large ignition source.

Date of ending the test 03-09-2024
Standard used EN 13772 (2011)
Product standard EN 13773 (2003)

Deviation from the standard -

Conditioning 20°C, relative humidity 65%

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure.

Length

	Front	Back	Front	Front
Severance 1 st thread	no	no	no	no
Severance 2 nd thread	no	no	no	no
Severance 3 rd thread	no	no	no	no
Time to sever 3 rd thread (s)	/	/	/	/
Destroyed length (mm)	130	125	130	130
Flaming debris	no	no	no	no

Width

	Front	Back	Back	Back
Severance 1 st thread	no	no	no	no
Severance 2 nd thread	no	no	no	no
Severance 3 rd thread	no	no	no	no
Time to sever 3 rd thread (s)	/	/	/	/
Destroyed length (mm)	125	130	130	130
Flaming debris	no	no	no	no

Classification in accordance with EN 13773 Class 1