



CERTIFICATE

CENTEXBEL TYPE TESTING | TEST REPORT N° 22.06073.05

According to report N° 22.06073.05, dated on 26/01/2023, we confirm that the below mentioned items were tested at CENTEXBEL with reference to **NF P 92-507 (2004) "Fire safety - Building - Interior fitting materials - Classification according to their reaction to fire"**.

The items show

Classification M1

When properly applied.

The evaluation of the burning behaviour is based on CENTEXBEL's evaluation scheme.

SAMPLES

1308

Various colours

Company

ADO Goldkante GmbH & Co. KG

Zimmersmühlenweg 14-18

61440 OBERURSEL - GERMANY

This Certificate is valid until 26/01/2028

Centexbel | Technologiepark 70 | BE 9052 Gent | Belgium, 26/01/2023

Stijn Devaere, PhD
Director Services



ADO Goldkante GmbH & Co. KG
Zimmersmühlenweg 14-18
61440 OBERURSEL
Germany

Your notice of
 15-11-2022

Your reference

Date
 26-01-2023

Analysis Report 22.06073.05

Required tests :

NF P92-507 (2004)

Sample id	Information given by the client	Date of receipt
T2222492	1308 - col. 110	15-11-2022
T2224278	1308 - col. 996	06-12-2022
T2301548	1308 - col. 575	19-01-2023



Gina Créelle
Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.
 The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.
 In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.



Reference: T2222492 - 1308 - col. 110
 T2224278 - 1308 - col. 996
 T2301548 - 1308 - col. 575

Classification of materials according to their reaction to fire - "Electric burner"

Date of ending the test 24-01-2023
 Standard used NF P92-503 (1995)
 Product standard NF P92-507 (2004)

Deviation from the standard A limited number of specimens have been tested for each sample.

Dimension of the specimens 600 mm x 180 mm x 1 mm
 Weight (g/m²)
 T2222492: 420
 T2224278: 427
 T2301548: 436

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure

Conditioning 23°C, relative humidity 50%
 Minimum 7 days or until constant mass is achieved

T2222492

	Length		Width	
	Front	Back	Front	Back
Hole formation	yes			yes
Max. afterflame time (s)	0	-	-	0
Afterglow	no			no
Afterglow with propagation in area > 25 cm	no			no
Damaged length (cm)	14.5	-	-	13.5
Damaged width (cm) in area >45 cm	0	-	-	0
Flaming molten droplets	no			no
Non-flaming molten droplets	no			no
Flaming debris	no			no
Non-flaming debris	no			no

T2224278

	Length		Width	
	Front	Back	Front	Back
Hole formation		yes	yes	
Max. afterflame time (s)	-	0	0	-
Afterglow		no	no	
Afterglow with propagation in area > 25 cm		no	no	
Damaged length (cm)	-	14.0	14.0	-
Damaged width (cm) in area >45 cm	-	0	0	-
Flaming molten droplets		no	no	
Non-flaming molten droplets		no	yes	
Flaming debris		no	no	
Non-flaming debris		no	no	

T2301548

	Length		Width	
	Front	Back	Front	Back
Hole formation	yes	yes	yes	yes
Max. afterflame time (s)	2	0	0	5
Afterglow	no	no	no	no
Afterglow with propagation in area > 25 cm	no	no	no	no
Damaged length (cm)	14.0	14.5	14.5	14.5
Damaged width (cm) in area >45 cm	0	0	0	0
Flaming molten droplets	no	no	no	no
Non-flaming molten droplets	yes	no	yes	yes
Flaming debris	no	no	no	no
Non-flaming debris	no	no	no	no



Reference: T2222492 - 1308 - col. 110
 T2224278 - 1308 - col. 996
 T2301548 - 1308 - col. 575

Classification of materials according to their reaction to fire - "Flame persistence test"

Date of ending the test	25-01-2023
Standard used	NF P92-504 (1995)
Product standard	NF P92-507 (2004)
Deviation from the standard	A limited number of specimens have been tested for each sample.
Dimension of the specimens	460 mm x 230 mm x 1 mm
Weight (g/m ²)	T2222492: 420 T2224278: 427 T2301548: 436

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure

Conditioning 23°C, relative humidity 50%
 Minimum 7 days or until constant mass is achieved

Each test has been carried out with a flame application time of 5s.

T2222492

	Length		Width	
	Front	Back	Front	Back
#1	*			*
#2	*			*
#3	*			*
#4	*			*
#5	*			*
#6	*			*
#7	*			*
#8	*			*
#9	*			*
#10	*			*

Flaming debris no
 Non-flaming debris no

*: afterflame time ≤ 2 s
 > 2 s: afterflame time > 2 s and ≤ 5 s
 > 5 s: afterflame time > 5 s

T2224278

	Length		Width	
	Front	Back	Front	Back
#1		*	*	
#2		*	*	
#3		*	*	
#4		*	*	
#5		*	*	
#6		*	*	
#7		*	*	
#8		*	*	
#9		*	*	
#10		*	*	

Flaming debris no
 Non-flaming debris no

*: afterflame time ≤ 2 s
 > 2 s: afterflame time > 2 s and ≤ 5 s
 > 5 s: afterflame time > 5 s



T2301548

	Length		Width	
	Front	Back	Front	Back
#1	*			*
#2	*			*
#3	*			*
#4	*			*
#5	*			*
#6	*			*
#7	*			*
#8	*			*
#9	*			*
#10	*			*

Flaming debris no
 Non-flaming debris no

*: afterflame time ≤ 2 s
 > 2 s: afterflame time > 2 s and ≤ 5 s
 > 5 s: afterflame time > 5 s



Reference: T2222492 - 1308 - col. 110
 T2224278 - 1308 - col. 996
 T2301548 - 1308 - col. 575

Classification of materials according to their reaction to fire - "Test for melting materials"

Date of ending the test 25-01-2023
 Standard used NF P92-505 (1995)
 Product standard NF P92-507 (2004)

Deviation from the standard A limited number of specimens have been tested for each sample.

Dimension of the specimens 70 mm x 70 mm x 1 mm
 Number of layers 1
 Weight (g/m²)
 T2222492: 420
 T2224278: 427
 T2301548: 436

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure

Conditioning 23°C, relative humidity 50%
 Minimum 7 days or until constant mass is achieved

T2222492

		First ignition (s)	Non-flaming debris	Flaming debris	Ignition cotton wool	Mass (g)
#1	front	*	yes	no	no	2.2
#2	back	*	yes	no	no	2.2
#3						
#4						

* no ignition

T2224278

		First ignition (s)	Non-flaming debris	Flaming debris	Ignition cotton wool	Mass (g)
#1	front	*	yes	no	no	2.3
#2	back	*	yes	no	no	2.3
#3						
#4						

* no ignition



T2301548

		First ignition (s)	Non-flaming debris	Flaming debris	Ignition cotton wool	Mass (g)
#1	front	*	yes	no	no	2.3
#2	back	*	yes	no	no	2.3
#3						
#4						

* no ignition