

Test laboratory for the fire behavior of building materials
Testing, supervising and certifying body, authorized by the building supervision authority

TEST REPORT

PZ-Hoch-260171-2

for the proof of fire behaviour according to DIN 4102, part 1

Translation of the German test report – no guarantee for translation of technical terms

company	Zimmer + Rohde GmbH Zimmermühlenweg 14-18 D-61440 Oberursel
description of samples	tree-layer fabric of 100 % IFR PES, white
name of the material	„1311“
sampling	by the company itself
content of request	Proof of flammability to classify building materials to class B1 (“schwerentflammbar”) according to DIN 4102, part 1
validity of test report	31.01.2031
result	The examined product meets the requirements of class B1 for hardly flammable (“schwerentflammbare”) building materials according to DIN 4102, pt. 1 (May 1998), suspended freely or with distance of >40 mm to same or other plain materials.

This test report includes 4 pages and 3 enclosures.

Remark: If the building material mentioned above is not used as a product according to MBO § 2, Abs. 9, Ziffer 1, there is no need for a general building supervisory test report.

This test report is not valid if the examined building material is used as product as defined by State Building Prescriptions (MBO § 17, Abs. 3).

This test report does not replace an eventually necessary proof of applicability concerning building supervisory or building laws as defined by State Building Prescriptions. This has to be certified instead by:

- “*allgemeine bauaufsichtliche Zulassung*” (General Building Inspectorate Approval) or by
- “*allgemeines bauaufsichtliches Prüfzeugnis*” (General Building Inspectorate Certificate) or by
- “*Zustimmung im Einzelfall*” (Exceptional Approval)

This test report can underlie building supervisory procedures

- for regular building products for the prescribed proofs of conformity
- for irregular building products for the required proofs of applicability.

Without written consent of the test laboratory, this test report may only be published or duplicated during its denoted period of validity, providing that no changes to appearance or content are made.

1. Description of test material in condition as delivered

PN 43406 "1311"

white fabric made of 100 % IFR PES

There is no difference between side A and side B

characteristic values determined by the test laboratory:

thickness: about 0,79 mm

area weight: about 296 g/m²

The testing laboratory is not provided with further details concerning composition of the tested building materials. Samples are deposited.

2. Preparation of samples

Samples with a size of 1000 mm and 190 mm where cut from the material for fire testing.

The samples were kept in climate chamber 23/50 until they reached constant weight.

3. Arrangement of samples

-freely suspended

#1365: **side A in warp direction**
#1366: **side B in weft direction**

4. Date of test CW 6 in 2026

5. Results The test has been performed according to DIN 4102 (Mai 1998)

line no.	Measurement	Result with the tested specimen			Dim.
	Test number	#1365	#1366	-	
	flaming direction	warp	weft	-	
	side	A	B	-	
1	Number of specimen arrangement acc. to. DIN 4102/T15, schedule 1	1	1	-	
2	Maximum flame height	30	30	-	cm
3	Time ¹⁾	0:02	0:02	-	min:s
4	Burn-through / melting ¹⁾	0:04	0:04	-	min:s
	Observations on the back side				
5	Flames / Glowing ¹⁾	-/-	-/-	-	min:s
6	Change of colour ¹⁾	-/-	-/-	-	min:s
7	Falling of burning droplets ¹⁾	-/-	-/-	-	
8	sporadic falling of burning droplets ²⁾	--	--	-	min:s
9	continuous falling of burning droplets ²⁾	--	--	-	min:s
10	Falling of burning parts ¹⁾	-/-	-/-	-	min:s
11	sporadic falling of burning parts ²⁾	--	--	-	
12	continuous falling of burning parts ²⁾	--	--	-	
13	Burning duration at sieve plate (max.)	-/-	-/-	-	min:s
14	Impairment of burner by material ¹⁾	-/-	-/-	-	min:s
15	End of burning at the specimen ¹⁾	1:40	0:50	-	min:s
16	Time of eventually end of test ¹⁾	-/-	-/-	-	min:s
17	Afterburning after end of test ¹⁾	-/-	-/-	-	min:s
18	Number of specimens	--	--	-	
19	Front side / Rear side of specimen ²⁾	--	--	-	
20	flame length	--	--	-	cm
21	Afterglow after end of test ¹⁾	-/-	-/-	-	min:s
22	Number of specimens	--	--	-	
23	Lower / Upper half of the specimen ²⁾	--	--	-	
24	Front side / Rear side of specimen ²⁾	--	--	-	
25	Density of smoke $\leq 400 \% * \text{min}$	1	1	-	%min
26	$> 400 \% * \text{min}^4)$	-	-	-	%min
27	Residual lengths: individual values ³⁾	Specimen 1 61 Specimen 2 65 Specimen 3 67 Specimen 4 62	64 64 65 65	-	cm cm cm cm
28	Average residual length ³⁾	64	65	-	cm
29	Maximum smoke temperature	123	122	-	°C
30	Time ¹⁾	09:48	09:45	-	min:s
31	Diagrams / photos in enclosure no.	1	2	-	
32	Remarks: - none -				

¹⁾ indication of times relative to beginning of test

²⁾ checked if applicable

³⁾ indication of carrier/foam layer separated in case of fire-proofing agents

⁴⁾ very strong development of smoke

6. Explanations concerning the testing procedure

The remaining tests could be skipped as the residual lengths exceeded 45 cm.

7. Summary of results and additional establishments to Fire Behaviour

lineno	Measurement	Result with the tested specimen			dimension
		#1365	1366	-	
flaming	test-no.	A	B	-	
	Side	warp	weft	-	
	Direction				
1	residual length	64	65	-	cm
2	max. smoke temperature	123	122	-	°C
3	integral of smoke density	1	1	-	%min
4	remarks: none				

According to DIN 4102, pt. 1, hardly flammable ("schwerentflammbare") building materials must meet the requirements of class B2.

After performing additional tests in the ignitability apparatus, this could be verified (encl. 3).

8. Special remarks

- This report is only valid for the material as described in paragraph 1. In combination with other materials or with additional coatings or primers etc., the burning behaviour may differ.
- This test report is not valid for the exposure to outdoor climate conditions, washing or cleaning with chemicals.
- This test report is not valid if the material is used as a building product in the sense of the State Building Regulations ("Landesbauordnungen", MBO § 17, par. 3).
- This test report is no substitute for a General Building Inspectorate Certificate.
- This test report is granted without prejudice to the rights of third parties, in particular private proprietary rights.
- For legal interests, only the German original version is relevant.
- In General Building Inspectorates procedures, this test report can be used for
 - regular building materials for the required proof of accordance
 - for not regular building materials for the required proof of applicability
- Changes in the report with index -2: name and address of the company & name of the material.

9. Validity

This test report is valid until the denoted date on page 1. The test report becomes invalid in case the standards on which these tests are based are changed.

Fladungen, 18.03.2026

Clerk in charge:



(Silke Biendara)




Head of test laboratory:



(Dipl.-Ing. (FH) Andreas Hoch)

Fire shaft test #1365




measurement


#1365, PN43406: A + K

Max. flue temperature: 123°C, Smoke density integral: 1%/min

Residual length: 64 cm



Fire shaft test #1366




measurement

#1366, PN43406: B + S

Max. flue temperature: 122°C, Smoke density integral: 1%/min

Residual length: 65 cm



**Test for normal flammability
classifying B2 according to DIN 4102**

1. Description of test material in condition as delivered cf. page 2

2. Preparation of samples

Samples for the ignitability apparatus were cut from the sample. The samples were kept in a climate 23/50 until they reached constant weight.

3. Arrangement of samples freely suspended

4. Date of test CW 6 in 2026

5. Results

PN43406	surface-test								Dim
samples no.	1	2	3	4	5	6	7	8	
side and direction	AL	BL	AQ	BQ	AL	AL	AL	AL	
ignition ¹⁾	1	1	1	1	1	1	1	1	s
measurement mark reached ¹⁾²⁾	./.	./.	./.	./.	./.	./.	./.	./.	s
maximum flame height	7	3	4	5	5	4	3	3	cm
time of max. flame height	8	5	4	5	4	4	4	4	s
self-cessation of flames ¹⁾	15	6	5	6	4	5	5	4	s
flames were extinguished ¹⁾	-/-	-/-	-/-	-/-	-/-	-/-	-/-	-/-	s
smoke development (visually)	low								
dropping of burning material ¹⁾²⁾	-/-	-/-	-/-	-/-	-/-	-/-	-/-	-/-	s
appearance after test: burned out till max. width 2 cm x height 8,5 cm									

PN43406	edge-test								Dim
samples no.	1	2	3	4	5	6	7	8	
side and direction	AL	BL	AQ	BQ	-	-	-	-	
ignition ¹⁾	2	2	2	2	-	-	-	-	s
measurement mark reached ¹⁾²⁾	./.	./.	./.	./.	-	-	-	-	s
maximum flame height	5	5	6	3	-	-	-	-	cm
time of max. flame height	6	6	6	4	-	-	-	-	s
self-cessation of flames ¹⁾	8	13	8	6	-	-	-	-	s
flames were extinguished ¹⁾	-/-	-/-	-/-	-/-	-	-	-	-	s
smoke development (visually)	very low								
dropping of burning material ¹⁾²⁾	-/-	-/-	-/-	-/-	-	-	-	-	s
appearance after test: burned out till max. width 2 cm x height 8,5 cm									

¹⁾ time denoted relative to beginning of test

²⁾ during 20 Sec

-/- no occurrence

-- no information

6. Remarks and explanations to the testing procedure - none -

7. Opinion concerning the dropping of burning material

The test for normal flammability shows no dropping burning material.

----- End of enclosures -----