



**Zimmer + Rohde GmbH**  
**Zimmersmühlenweg 14-18**  
**61440 Oberursel**  
**Germany**

**Your notice of**  
31-03-2026

**Your reference**

**Date**  
13-05-2026

## Analysis Report 26.01726.10


### Modification

Required tests :  
**EN 13773 (2003)**

Sample id	Updated information given by the client	Date of receipt
T2606732	A1311	31-03-2026

Gina Créelle  
Order responsible


This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.  
The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.  
In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.



## Samples

T2606732  
A1311






**Reference: T2606732 - A1311**

**Washing and drying**

Date of ending the test	15-04-2026
Standard used	ISO 6330 (2000) + A1 (2008), ISO 6330 (2012)
Deviation from the standard	-
Conditioning	20°C, relative humidity 65%
Apparatus	Wascator FOM 71 (type A)
Used detergent	ECE detergent (Type 3)
Washing method and temperature	8A- 30°C (2000)
Drying method	A = Line dry (2000)
Number of washing cycles	1
Mass of the test specimens	204 g
Mass of the ballast	The washing machine is filled with ballast to achieve 2 kg in total
Remark	Washing always occurs with a ballast type III 100% PES regardless of the composition of the fabric.

Sample generated: T2606732\_01d



**Reference:** T2606732\_01d - A1311

**Textiles – Burning behaviour – Curtains and drapes - Textile fabrics - Determination of the ignitability of vertically oriented specimens.**

Date of ending the test 11-05-2026  
Standard used EN 1101 (1995) + A1 (2005)  
Product standard EN 13773 (2003)

Deviation from the standard -

Conditioning 20°C, relative humidity 65%  
Testing atmosphere 22°C, relative humidity 40%

Dimension of the specimens 200 mm x 80 mm


Ignition Bottom edge

The test specimens have been cleaned.

**Length**

Flame application time (s)	Cases of ignition	Cases of non-ignition
1	0	1
2	0	1
3	0	1
4	0	1
5	0	1
10	0	1
15	0	1
20	0	5

The mean of the recorded times at which ignition was observed is calculated  
No ignition within 20 s



Width

Flame application time (s)	Cases of ignition	Cases of non-ignition
1	0	1
2	0	1
3	0	1
4	0	1
5	0	1
10	0	1
15	0	1
20	0	5

The mean of the recorded times at which ignition was observed is calculated  
 No ignition within 20 s

Minimum ignition time

No ignition within 20 s

Reference: T2606732 - A1311

**Textiles and textile products – Burning behaviour – Curtains and drapes. Measurement of flame spread of vertically oriented specimens with large ignition source.**

Date of ending the test 12-05-2026  
Standard used EN 13772 (2011)  
Product standard EN 13773 (2003)

Deviation from the standard -

Conditioning 20°C, relative humidity 65%

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure.

**Length**

	Front	Back	Back	Back
Severance 1 <sup>st</sup> thread	no	no	no	no
Severance 2 <sup>nd</sup> thread	no	no	no	no
Severance 3 <sup>rd</sup> thread	no	no	no	no
Time to sever 3 <sup>rd</sup> thread (s)	/	/	/	/
Destroyed length (mm)	105	115	120	110
Flaming debris	no	no	no	no

**Width**

	Front	Back	Back	Back
Severance 1 <sup>st</sup> thread	no	no	no	no
Severance 2 <sup>nd</sup> thread	no	no	no	no
Severance 3 <sup>rd</sup> thread	no	no	no	no
Time to sever 3 <sup>rd</sup> thread (s)	/	/	/	/
Destroyed length (mm)	125	130	120	120
Flaming debris	no	no	no	no

**Reference:** T2606732 - A1311

**Washing and drying**

Date of ending the test	15-04-2026
Standard used	ISO 6330 (2000) + A1 (2008), ISO 6330 (2012)
Deviation from the standard	-
Conditioning	20°C, relative humidity 65%
Apparatus	Wascator FOM 71 (type A)
Used detergent	ECE detergent (Type 3)
Washing method and temperature	8A- 30°C (2000)
Drying method	A = Line dry (2000)
Number of washing cycles	12
Mass of the test specimens	285 g
Mass of the ballast	The washing machine is filled with ballast to achieve 2 kg in total
Remark	Washing always occurs with a ballast type III 100% PES regardless of the composition of the fabric.

Sample generated: T2606732\_02d

Reference: T2606732\_02d - A1311

**Textiles and textile products – Burning behaviour – Curtains and drapes. Measurement of flame spread of vertically oriented specimens with large ignition source.**

Date of ending the test 12-05-2026  
Standard used EN 13772 (2011)  
Product standard EN 13773 (2003)

Deviation from the standard -

Conditioning 20°C, relative humidity 65%

The test specimens have been cleaned.

**Length**

	Front	Back	Front	Front
Severance 1 <sup>st</sup> thread	no	no	no	no
Severance 2 <sup>nd</sup> thread	no	no	no	no
Severance 3 <sup>rd</sup> thread	no	no	no	no
Time to sever 3 <sup>rd</sup> thread (s)	/	/	/	/
Destroyed length (mm)	135	110	140	135
Flaming debris	no	no	no	no

**Width**

	Front	Back	Front	Front
Severance 1 <sup>st</sup> thread	no	no	no	no
Severance 2 <sup>nd</sup> thread	no	no	no	no
Severance 3 <sup>rd</sup> thread	no	no	no	no
Time to sever 3 <sup>rd</sup> thread (s)	/	/	/	/
Destroyed length (mm)	135	115	115	115
Flaming debris	no	no	no	no



**Reference: T2606732 - A1311**

**Classification of curtains and drapes according to EN 13773**

Product standard EN 13773 (2003)

Classification in accordance with EN 13773 Class 1