

CERTIFICATE

CENTEXBEL TYPE TESTING | TEST REPORT N° 22.00470.10

According to report N° 22.00470.10, dated on 23/02/2022, we confirm that the below mentioned items were tested at CENTEXBEL with reference to **NF P 92-507 (2004) "Fire safety - Building - Interior fitting materials - Classification according to their reaction to fire"**.

The items show

Classification M1

When properly applied.

The evaluation of the burning behaviour is based on CENTEXBEL's evaluation scheme.

SAMPLES

1359

Various colours

Company

Ado Goldkante GmbH Co Kg

Zimmersmühlenweg 14-18

61440 OBERURSEL - GERMANY

This Certificate is valid until 23/02/2027

Centexbel | Technologiepark 70 | BE 9052 Gent | Belgium, 23/02/2022

Stijn Devaere, PhD
Director Services



ADO Goldkante GmbH & Co. KG
Zimmersmühlenweg 14-18
61440 OBERURSEL
Germany

Your notice of
 26-01-2022

Your reference

Date
 23-02-2022

Analysis Report 22.00470.10

Required tests :

NF P92-507 (2004)

Sample id	Information given by the client	Date of receipt
T2201631	Art : 1359 - col : 998	26-01-2022
T2201632	Art : 1359 - col : 111	26-01-2022
T2202110	Art : 1359 - col : 555	26-01-2022

Mike De Vrieze
 Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.
 The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.
 In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.



Reference: T2201631 - Art : 1359 - col : 998
 T2201632 - Art : 1359 - col : 111
 T2202110 - Art : 1359 - col : 555

Classification of materials according to their reaction to fire - "Electric burner"

Date of ending the test 16-02-2022
 Standard used NF P92-503 (1995)
 Product standard NF P92-507 (2004)

Deviation from the standard A limited number of specimens have been tested for each sample.

Dimension of the specimens 600 mm x 180 mm x < 1 mm
 Weight (g/m²)
 T2201631: 268
 T2201632: 269
 T2202110: 267

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure

Conditioning 23°C, relative humidity 50%
 Minimum 7 days or until constant mass is achieved

T2201631


	Length		Width	
	Face A	Face B	Face A	Face B
Hole formation	yes			yes
Max. afterflame time (s)	0	-	-	0
Afterglow	no			no
Afterglow with propagation in area > 25 cm	no			no
Damaged length (cm)	14.5	-	-	13.5
Damaged width (cm) in area >45 cm	0	-	-	0
Flaming molten droplets	no			no
Non-flaming molten droplets	no			no
Flaming debris	no			no
Non-flaming debris	no			no

T2201632

	Length		Width	
	Face A	Face B	Face A	Face B
Hole formation		yes	yes	
Max. afterflame time (s)	-	0	0	-
Afterglow		no	no	
Afterglow with propagation in area > 25 cm		no	no	
Damaged length (cm)	-	14.0	13.0	-
Damaged width (cm) in area >45 cm	-	0	0	-
Flaming molten droplets		no	no	
Non-flaming molten droplets		no	no	
Flaming debris		no	no	
Non-flaming debris		no	no	

T2202110

	Length		Width	
	Face A	Face B	Face A	Face B
Hole formation	yes			yes
Max. afterflame time (s)	0	-	-	0
Afterglow	no			no
Afterglow with propagation in area > 25 cm	no			no
Damaged length (cm)	13.0	-	-	14.0
Damaged width (cm) in area >45 cm	0	-	-	0
Flaming molten droplets	no			no
Non-flaming molten droplets	no			no
Flaming debris	no			no
Non-flaming debris	no			no



Reference: T2201631 - Art : 1359 - col : 998
 T2201632 - Art : 1359 - col : 111
 T2202110 - Art : 1359 - col : 555

Classification of materials according to their reaction to fire - "Flame persistence test"

Date of ending the test	21-02-2022
Standard used	NF P92-504 (1995)
Product standard	NF P92-507 (2004)
Deviation from the standard	A limited number of specimens have been tested for each sample.
Dimension of the specimens	460 mm x 230 mm x < 1 mm
Weight (g/m ²)	T2201631:268 T2201632:269 T2202110 :267

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure

Conditioning 23°C, relative humidity 50%
 Minimum 7 days or until constant mass is achieved

Each test has been carried out with a flame application time of 5s.

T2201631

	Length		Width	
	Face A	Face B	Face A	Face B
#1	*			*
#2	*			*
#3	*			*
#4	*			*
#5	*			*
#6	*			*
#7	*			*
#8	*			*
#9	*			*
#10	*			*

Flaming debris no
 Non-flaming debris no

*: afterflame time ≤ 2 s
 > 2 s: afterflame time > 2 s and ≤ 5 s
 > 5 s: afterflame time > 5 s

T2201632

	Length		Width	
	Face A	Face B	Face A	Face B
#1		*	*	
#2		*	*	
#3		*	*	
#4		*	*	
#5		*	*	
#6		*	*	
#7		*	*	
#8		*	*	
#9		*	*	
#10		*	*	

Flaming debris no
 Non-flaming debris yes

*: afterflame time ≤ 2 s
 > 2 s: afterflame time > 2 s and ≤ 5 s
 > 5 s: afterflame time > 5 s

	Length		Width	
	Face A	Face B	Face A	Face B
#1	*			*
#2	*			*
#3	*			*
#4	*			*
#5	*			*
#6	*			*
#7	*			*
#8	*			*
#9	*			*
#10	*			*

```

*: afterflame time  $\leq 2$  s
> 2 s: afterflame time > 2 s and  $\leq 5$  s
> 5 s: afterflame time > 5 s

```




Reference: T2201631 - Art : 1359 - col : 998
 T2201632 - Art : 1359 - col : 111
 T2202110 - Art : 1359 - col : 555

Classification of materials according to their reaction to fire - "Test for melting materials"

Date of ending the test 22-02-2022
 Standard used NF P92-505 (1995)
 Product standard NF P92-507 (2004)

Deviation from the standard A limited number of specimens have been tested for each sample.

Dimension of the specimens 70 mm x 70 mm x 1 mm
 Number of layers 2
 Weight (g/m²) T2201631: 268
 T2201632: 269
 T2202110: 267

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure

Conditioning 23°C, relative humidity 50%
 Minimum 7 days or until constant mass is achieved

T2201631

		First ignition (s)	Non-flaming debris	Flaming debris	Ignition cotton wool	Mass (g)
#1	face A	*	yes	no	no	2.8
#2	face B	*	yes	no	no	2.8
#3						
#4						

* no ignition

T2201632

		First ignition (s)	Non-flaming debris	Flaming debris	Ignition cotton wool	Mass (g)
#1	face A	*	yes	no	no	2.8
#2	face B	*	yes	no	no	2.9
#3						
#4						

* no ignition



T2202110

		First ignition (s)	Non-flaming debris	Flaming debris	Ignition cotton wool	Mass (g)
#1	face A	*	yes	no	no	2.8
#2	face B	*	yes	no	no	2.8
#3						
#4						

* no ignition