



## Test Report

No.: HKSL1510165295TX

Date: Oct 23, 2015

Page 1 of 2

ADO  
ZIMMERSMUHLENWEG 14-18,  
61440 OBERURSEL/FRANKFURT, GERMANY

The following sample was submitted and identified by the client as:

One sample of weave cutting in 999 for upholstery.

Buyer	:	Worldwide
Application No.	:	ADO004
Brand	:	ADO
Colour	:	999
End Use	:	Upholstery
Item No.	:	1511
Model No.	:	BELCANTO
Fabric Width	:	140cm
Fabric Weight	:	444 gram
Season	:	Spring 2016
Country Of Destination	:	Worldwide

Sample Receiving Date	:	Oct 16, 2015
Test Performing Period	:	Oct 17, 2015 – Oct 23, 2015

Test Performed	:	Selected test(s) as requested by applicant (details please refer to result page(s)).
----------------	---	--

\* \* \* \*

Test Results	:	Please refer to the next page(s).
--------------	---	-----------------------------------

Residual & tested samples returned to applicant

Signed for and on behalf of  
SGS Hong Kong Ltd.

Liu Wang, Andy  
Assistant Technical Manager

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.



## Test Report

No.: HKSL1510165295TX

Date: Oct 23, 2015

Page 2 of 2

### Test Results :

#### Abrasion Resistance

(ISO 12947-2-1998 / Cor.1:2002; Martindale Wear & Abrasion Tester ; 12 kPa Pressure)

End point (rubs)

32000

Specified  
Requirement  
Exceeds 55000

\*\*\* End of Report \*\*\*

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.