



## Test Report

No.: SL118002699303TX

Date: Aug 23, 2018

Page 1 of 2

ADO GOLDKANTE GMBH & CO. KG  
ZIMMERSMUHLENWEG 14-18  
OBERURSEL, D-61440, Germany

The following sample was submitted and identified on behalf of the buyer as:

One sample of woven 23% pan 77% pes missori.

Buyer	:	Worldwide
Brand	:	ADO
Application No.	:	CET-RY001-KB5
Fibre Content	:	23% pan 77% pes
Style No.	:	#1569 MISSORI
Item No.	:	1569
Fabric Width	:	140 cm
Country Of Destination	:	HK / Asia / ME / International
Sample Receiving Date	:	Aug 14, 2018
Test Performing Period	:	Aug 14, 2018 – Aug 23, 2018
Test Performed	:	Selected test(s) as requested by applicant against specified requirement (details please refer to result page(s)).

\* \* \* \*

Test Results : Please refer to the next page(s).

Signed for and on behalf of  
SGS Hong Kong Ltd.

Poon Wai Man, Lolita  
Assistant Technical Manager

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.





## Test Report

No.: SL118002699303TX

Date: Aug 23, 2018

Page 2 of 2

### Test Results :

#### Abrasion Resistance

(ISO 12947-2-2016; Martindale Wear & Abrasion Tester ; 9 kPa Pressure)

End point (rubs)

65000

Specified  
Requirement  
Exceeds  
100,000

\*\*\* End of Report \*\*\*

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.