



# CERTIFICATE

## **CENTEXBEL TYPE TESTING | TEST REPORT N° 22.01552.01**

According to report N° 22.01552.01, dated on 15/04/2022, we confirm that the below mentioned items were tested at CENTEXBEL with reference to **NF P 92-507 (2004) "Fire safety - Building - Interior fitting materials - Classification according to their reaction to fire"**.

The items show

## **Classification M1**

When properly applied.

The evaluation of the burning behaviour is based on CENTEXBEL's evaluation scheme.

### **SAMPLES**

2510

Various colours

### **Company**

Ado Goldkante GmbH Co Kg  
Zimmersmühlenweg 14-18  
61440 OBERURSEL - GERMANY

This Certificate is valid until 15/04/2027

Centexbel | Technologiepark 70 | BE 9052 Gent | Belgium, 19/04/2022

Stijn Devaere, PhD  
Director Services



**ADO Goldkante GmbH & Co. KG**  
**Zimmersmühlenweg 14-18**  
**61440 OBERURSEL**  
**Germany**

**Your notice of**  
 21-03-2022

**Your reference**

**Date**  
 15-04-2022

## Analysis Report 22.01552.01

Required tests :

**NF P92-507 (2004)**

| Sample id | Information given by the client | Date of receipt |
|-----------|---------------------------------|-----------------|
| T2205427  | 2510 - col 200                  | 21-03-2022      |
| T2205428  | 2510 - col 665                  | 21-03-2022      |
| T2205429  | 2510 - col 553                  | 21-03-2022      |



**Gina Créelle**  
**Order responsible**

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.  
 The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.  
 In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.



**Reference:** T2205427 - 2510 - col 200  
 T2205428 - 2510 - col 665  
 T2205429 - 2510 - col 553

**Classification of materials according to their reaction to fire - "Electric burner"**

Date of ending the test 14-04-2022  
 Standard used NF P92-503 (1995)  
 Product standard NF P92-507 (2004)

Deviation from the standard A limited number of specimens have been tested for each sample.

Dimension of the specimens 600 mm x 180 mm x 1 mm  
 Weight (g/m<sup>2</sup>)  
 T2205427:127  
 T2205428:116  
 T2205429:127

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure

Conditioning 23°C, relative humidity 50%  
 Minimum 7 days or until constant mass is achieved

T2205427

|  | Length |      | Width |      |
|--|--------|------|-------|------|
|  | Front  | Back | Front | Back |
| Hole formation                             | yes    |      |       | yes  |
| Max. afterflame time (s)                   | 0      | -    | -     | 0    |
| Afterglow                                  | no     |      |       | no   |
| Afterglow with propagation in area > 25 cm | no     |      |       | no   |
| Damaged length (cm)                        | 18.0   | -    | -     | 16.0 |
| Damaged width (cm) in area >45 cm          | 0      | -    | -     | 0    |
| Flaming molten droplets                    | no     |      |       | no   |
| Non-flaming molten droplets                | yes    |      |       | no   |
| Flaming debris                             | no     |      |       | no   |
| Non-flaming debris                         | no     |      |       | no   |

### T2205428

|  | Length |      | Width |      |
|--|--------|------|-------|------|
|  | Front  | Back | Front | Back |
| Hole formation                             |        | yes  | yes   |      |
| Max. afterflame time (s)                   | -      | 0    | 0     | -    |
| Afterglow                                  |        | no   | no    |      |
| Afterglow with propagation in area > 25 cm |        | no   | no    |      |
| Damaged length (cm)                        | -      | 18.5 | 16.0  | -    |
| Damaged width (cm) in area >45 cm          | -      | 0    | 0     | -    |
| Flaming molten droplets                    |        | no   | no    |      |
| Non-flaming molten droplets                |        | no   | no    |      |
| Flaming debris                             |        | no   | no    |      |
| Non-flaming debris                         |        | no   | no    |      |

### T2205429

|  | Length |      | Width |      |
|--|--------|------|-------|------|
|  | Front  | Back | Front | Back |
| Hole formation                             | yes    |      |       | yes  |
| Max. afterflame time (s)                   | 0      | -    | -     | 2    |
| Afterglow                                  | no     |      |       | no   |
| Afterglow with propagation in area > 25 cm | no     |      |       | no   |
| Damaged length (cm)                        | 20.5   | -    | -     | 19.0 |
| Damaged width (cm) in area >45 cm          | 0      | -    | -     | 0    |
| Flaming molten droplets                    | no     |      |       | no   |
| Non-flaming molten droplets                | yes    |      |       | yes  |
| Flaming debris                             | no     |      |       | no   |
| Non-flaming debris                         | no     |      |       | no   |



**Reference:** T2205427 - 2510 - col 200  
 T2205428 - 2510 - col 665  
 T2205429 - 2510 - col 553

**Classification of materials according to their reaction to fire - "Flame persistence test"**

|                             |   |
|-----------------------------|---|
| Date of ending the test     | 15-04-2022  |
| Standard used               | NF P92-504 (1995)   |
| Product standard            | NF P92-507 (2004)   |
| Deviation from the standard | A limited number of specimens have been tested for each sample. |
| Dimension of the specimens  | 460 mm x 230 mm x 1 mm  |
| Weight (g/m <sup>2</sup> )  | T2205427: 127<br>T2205428: 116<br>T2205429: 127                 |

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure

Conditioning 23°C, relative humidity 50%  
 Minimum 7 days or until constant mass is achieved

Each test has been carried out with a flame application time of 5s.

### T2205427

|     | Length |      | Width |      |
|-----|--------|------|-------|------|
|     | Front  | Back | Front | Back |
| #1  | *      |      |       | *    |
| #2  | *      |      |       | *    |
| #3  | *      |      |       | *    |
| #4  | *      |      |       | *    |
| #5  | *      |      |       | *    |
| #6  | *      |      |       | *    |
| #7  | *      |      |       | *    |
| #8  | *      |      |       | *    |
| #9  | *      |      |       | *    |
| #10 | *      |      |       | *    |

Flaming debris no  
 Non-flaming debris no

\*: afterflame time  $\leq 2$  s  
 > 2 s: afterflame time > 2 s and  $\leq 5$  s  
 > 5 s: afterflame time > 5 s

### T2205428

|     | Length |      | Width |      |
|-----|--------|------|-------|------|
|     | Front  | Back | Front | Back |
| #1  |        | *    | *     |      |
| #2  |        | *    | *     |      |
| #3  |        | *    | *     |      |
| #4  |        | *    | *     |      |
| #5  |        | *    | *     |      |
| #6  |        | *    | *     |      |
| #7  |        | *    | *     |      |
| #8  |        | *    | *     |      |
| #9  |        | *    | *     |      |
| #10 |        | *    | *     |      |

Flaming debris no  
 Non-flaming debris no

\*: afterflame time  $\leq 2$  s  
 > 2 s: afterflame time > 2 s and  $\leq 5$  s  
 > 5 s: afterflame time > 5 s

|     | Length |      | Width |      |
|-----|--------|------|-------|------|
|     | Front  | Back | Front | Back |
| #1  | *      |      |       | *    |
| #2  | *      |      |       | *    |
| #3  | *      |      |       | *    |
| #4  | *      |      |       | *    |
| #5  | *      |      |       | *    |
| #6  | *      |      |       | *    |
| #7  | *      |      |       | *    |
| #8  | *      |      |       | *    |
| #9  | *      |      |       | *    |
| #10 | *      |      |       | *    |

```

*: afterflame time  $\leq 2$  s
> 2 s: afterflame time  $> 2$  s and  $\leq 5$  s
> 5 s: afterflame time  $> 5$  s

```



**Reference:** T2205427 - 2510 - col 200  
 T2205428 - 2510 - col 665  
 T2205429 - 2510 - col 553

**Classification of materials according to their reaction to fire - "Test for melting materials"**

|                             |   |
|-----------------------------|---|
| Date of ending the test     | 15-04-2022  |
| Standard used               | NF P92-505 (1995)   |
| Product standard            | NF P92-507 (2004)   |
| Deviation from the standard | A limited number of specimens have been tested for each sample. |
| Dimension of the specimens  | 70 mm x 70 mm x 2 mm  |
| Number of layers            | 4   |
| Weight (g/m <sup>2</sup> )  | T2205427: 127<br>T2205428: 116<br>T2205429: 127                 |

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure

Conditioning 23°C, relative humidity 50%  
 Minimum 7 days or until constant mass is achieved



T2205427

|    |       | First ignition (s) | Non-flaming debris | Flaming debris | Ignition cotton wool | Mass (g) |
|----|-------|--------------------|--------------------|----------------|----------------------|----------|
| #1 | front | *                  | yes                | no             | no                   | 2.7      |
| #2 | back  | *                  | yes                | no             | no                   | 2.6      |
| #3 |       |                    |                    |                |                      |          |
| #4 |       |                    |                    |                |                      |          |

\* no ignition

T2205428

|    |       | First ignition (s) | Non-flaming debris | Flaming debris | Ignition cotton wool | Mass (g) |
|----|-------|--------------------|--------------------|----------------|----------------------|----------|
| #1 | front | *                  | yes                | no             | no                   | 2.7      |
| #2 | back  | *                  | yes                | no             | no                   | 2.7      |
| #3 |       |                    |                    |                |                      |          |
| #4 |       |                    |                    |                |                      |          |

\* no ignition

T2205429

|    |       | First ignition (s) | Non-flaming debris | Flaming debris | Ignition cotton wool | Mass (g) |
|----|-------|--------------------|--------------------|----------------|----------------------|----------|
| #1 | front | *                  | yes                | no             | no                   | 2.7      |
| #2 | back  | *                  | yes                | no             | no                   | 2.8      |
| #3 |       |                    |                    |                |                      |          |
| #4 |       |                    |                    |                |                      |          |

\* no ignition