

**Zimmer + Rohde GmbH
Zimmersmühlenweg 14-18
61440 OBERURSEL
Deutschland**

Your notice of
19-11-2025

Your reference
5509356

Date
05-01-2026

Analysis Report 25.06340.03


Required tests :
EN 13773 (2003)

Sample id	Information given by the client	Date of receipt
T2524079	3011	19-11-2025



Gina Créelle
Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.
The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.
In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.




Reference: **T2524079 - 3011**

Washing and drying

Date of ending the test	26-11-2025
Standard used	ISO 6330 (2000) + A1 (2008), ISO 6330 (2012)
Deviation from the standard	-
Conditioning	20°C, relative humidity 65%
Apparatus	Wascator FOM 71 (type A)
Used detergent	ECE detergent (Type 3)
Washing method and temperature	8A- 30°C (2000)
Drying method	A = Line dry (2000)
Number of washing cycles	1
Mass of the test specimens	211 g
Mass of the ballast	The washing machine is filled with ballast to achieve 2 kg in total
Remark	Washing always occurs with a ballast type III 100% PES regardless of the composition of the fabric.

Sample generated: T2524079_01d



Reference: **T2524079_01d - 3011**

Textiles – Burning behaviour – Curtains and drapes - Textile fabrics - Determination of the ignitability of vertically oriented specimens.

Date of ending the test 22-12-2025
Standard used EN 1101 (1995) + A1 (2005)
Product standard EN 13773 (2003)

Deviation from the standard -

Conditioning 20°C, relative humidity 65%
Testing atmosphere 20°C, relative humidity 41%

Dimension of the specimens 200 mm x 80 mm


Ignition Bottom edge

The test specimens have been cleaned.

Length

Flame application time (s)	Cases of ignition	Cases of non-ignition
1	0	1
2	0	1
3	0	1
4	0	1
5	0	1
10	0	1
15	0	1
20	0	5

The mean of the recorded times at which ignition was observed is calculated
No ignition within 20 s




Width

Flame application time (s)	Cases of ignition	Cases of non-ignition
1	0	1
2	0	1
3	0	1
4	0	1
5	0	1
10	0	1
15	0	1
20	0	5

The mean of the recorded times at which ignition was observed is calculated
No ignition within 20 s

Minimum ignition time

No ignition within 20 s



Reference: **T2524079 - 3011**

Textiles and textile products – Burning behaviour – Curtains and drapes. Measurement of flame spread of vertically oriented specimens with large ignition source.

Date of ending the test 24-12-2025
 Standard used EN 13772 (2011)
 Product standard EN 13773 (2003)

Deviation from the standard -

Conditioning 20°C, relative humidity 65%


The test specimens have not been cleaned nor submitted to an accelerated ageing procedure.

Length

	Front	Back	Back	Back
Severance 1 st thread	no	no	no	no
Severance 2 nd thread	no	no	no	no
Severance 3 rd thread	no	no	no	no
Time to sever 3 rd thread (s)	/	/	/	/
Destroyed length (mm)	130	140	130	135
Flaming debris	no	no	no	no

Width

	Front	Back	Front	Front
Severance 1 st thread	no	no	no	no
Severance 2 nd thread	no	no	no	no
Severance 3 rd thread	no	no	no	no
Time to sever 3 rd thread (s)	/	/	/	/
Destroyed length (mm)	140	125	125	145
Flaming debris	no	no	no	no




Reference: **T2524079 - 3011**

Washing and drying

Date of ending the test	26-11-2025
Standard used	ISO 6330 (2000) + A1 (2008), ISO 6330 (2012)
Deviation from the standard	-
Conditioning	20°C, relative humidity 65%
Apparatus	Wascator FOM 71 (type A)
Used detergent	ECE detergent (Type 3)
Washing method and temperature	8A- 30°C (2000)
Drying method	A = Line dry (2000)
Number of washing cycles	12
Mass of the test specimens	179 g
Mass of the ballast	The washing machine is filled with ballast to achieve 2 kg in total
Remark	Washing always occurs with a ballast type III 100% PES regardless of the composition of the fabric.

Sample generated: T2524079_02d



Reference: **T2524079_02d - 3011**

Textiles and textile products – Burning behaviour – Curtains and drapes. Measurement of flame spread of vertically oriented specimens with large ignition source.

Date of ending the test 24-12-2025
Standard used EN 13772 (2011)
Product standard EN 13773 (2003)

Deviation from the standard -

Conditioning 20°C, relative humidity 65%


The test specimens have been cleaned.

Length

	Front	Back	Front	Front
Severance 1 st thread	no	no	no	no
Severance 2 nd thread	no	no	no	no
Severance 3 rd thread	no	no	no	no
Time to sever 3 rd thread (s)	/	/	/	/
Destroyed length (mm)	145	140	135	130
Flaming debris	no	no	no	no

Width

	Front	Back	Back	Back
Severance 1 st thread	no	no	no	no
Severance 2 nd thread	no	no	no	no
Severance 3 rd thread	no	no	no	no
Time to sever 3 rd thread (s)	/	/	/	/
Destroyed length (mm)	125	135	130	135
Flaming debris	no	no	no	no



Reference: **T2524079 - 3011**

Classification of curtains and drapes according to EN 13773

Product standard EN 13773 (2003)

Classification in accordance
with EN 13773 Class 1