



CERTIFICATE

CENTEXBEL TYPE TESTING | TEST REPORT N° 22.06073.02

According to report N° 22.06073.02, dated on 5/12/2022, we confirm that the below mentioned items were tested at CENTEXBEL with reference to **NF P 92-507 (2004) "Fire safety - Building - Interior fitting materials - Classification according to their reaction to fire"**.

The items show

Classification M1

When properly applied.

The evaluation of the burning behaviour is based on CENTEXBEL's evaluation scheme.

SAMPLES	3019 Various colours
Company	ADO Goldkante GmbH & Co. KG Zimmersmühlenweg 14-18 61440 OBERURSEL - GERMANY

This Certificate is valid until 5/12/2027

Centexbel | Technologiepark 70 | BE 9052 Gent | Belgium, 5/12/2022

A handwritten signature in blue ink, appearing to read 'Stijn Devaere'.

Stijn Devaere, PhD
Director Services



ADO Goldkante GmbH & Co. KG
Zimmersmühlenweg 14-18
61440 OBERURSEL
Germany

Your notice of
15-11-2022

Your reference

Date
05-12-2022

Analysis Report 22.06073.02

Required tests :

NF P92-507 (2004)

Sample id	Information given by the client	Date of receipt
T2222496	3019 - col. 110	15-11-2022
T2222497	3019 - col. 994	15-11-2022
T2222498	3019 - col. 736	15-11-2022

Gina Créelle
Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.
The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.
In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.

Reference: T2222496 - 3019 - col. 110
 T2222497 - 3019 - col. 994
 T2222498 - 3019 - col. 736

Classification of materials according to their reaction to fire - "Electric burner"

Date of ending the test 28-11-2022
 Standard used NF P92-503 (1995)
 Product standard NF P92-507 (2004)

Deviation from the standard A limited number of specimens have been tested for each sample.

Dimension of the specimens 600 mm x 180 mm x < 1 mm
 Weight (g/m²)
 T2222496: 91
 T2222497: 91
 T2222498: 92

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure

Conditioning 23°C, relative humidity 50%
 Minimum 7 days or until constant mass is achieved

T2222496

	Length		Width	
	Face A	Face B	Face A	Face B
Hole formation	yes			yes
Max. afterflame time (s)	0	-	-	0
Afterglow	no			no
Afterglow with propagation in area > 25 cm	no			no
Damaged length (cm)	16.0	-	-	15.0
Damaged width (cm) in area >45 cm	0	-	-	0
Flaming molten droplets	no			no
Non-flaming molten droplets	no			no
Flaming debris	no			no
Non-flaming debris	no			no

T2222497

	Length		Width	
	Face A	Face B	Face A	Face B
Hole formation		yes	yes	
Max. afterflame time (s)	-	0	0	-
Afterglow		no	no	
Afterglow with propagation in area > 25 cm		no	no	
Damaged length (cm)	-	15.0	15.5	-
Damaged width (cm) in area >45 cm	-	0	0	-
Flaming molten droplets		no	no	
Non-flaming molten droplets		no	no	
Flaming debris		no	no	
Non-flaming debris		no	no	

T2222498

	Length		Width	
	Face A	Face B	Face A	Face B
Hole formation	yes			yes
Max. afterflame time (s)	0	-	-	0
Afterglow	no			no
Afterglow with propagation in area > 25 cm	no			no
Damaged length (cm)	15.5	-	-	15.0
Damaged width (cm) in area >45 cm	0	-	-	0
Flaming molten droplets	no			no
Non-flaming molten droplets	no			no
Flaming debris	no			no
Non-flaming debris	no			no

Reference: T2222496 - 3019 - col. 110
T2222497 - 3019 - col. 994
T2222498 - 3019 - col. 736

Classification of materials according to their reaction to fire - "Flame persistence test"

Date of ending the test	29-11-2022
Standard used	NF P92-504 (1995)
Product standard	NF P92-507 (2004)
Deviation from the standard	A limited number of specimens have been tested for each sample.
Dimension of the specimens	460 mm x 230 mm x < 1 mm
Weight (g/m ²)	T2222496: 91 T2222497: 91 T2222498: 92

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure

Conditioning 23°C, relative humidity 50%
Minimum 7 days or until constant mass is achieved

Each test has been carried out with a flame application time of 5s.



T2222496

	Length		Width	
	Face A	Face B	Face A	Face B
#1	*			*
#2	*			*
#3	*			*
#4	*			*
#5	*			*
#6	*			*
#7	*			*
#8	*			*
#9	*			*
#10	*			*

Flaming debris no
Non-flaming debris yes

*: afterflame time ≤ 2 s
> 2 s: afterflame time > 2 s and ≤ 5 s
> 5 s: afterflame time > 5 s

T2222497

	Length		Width	
	Face A	Face B	Face A	Face B
#1		*	*	
#2		*	*	
#3		*	*	
#4		*	*	
#5		*	*	
#6		*	*	
#7		*	*	
#8		*	*	
#9		*	*	
#10		*	*	

Flaming debris no
Non-flaming debris yes

*: afterflame time ≤ 2 s
> 2 s: afterflame time > 2 s and ≤ 5 s
> 5 s: afterflame time > 5 s



T2222498

	Length		Width	
	Face A	Face B	Face A	Face B
#1	*			*
#2	*			*
#3	*			*
#4	*			*
#5	*			*
#6	*			*
#7	*			*
#8	*			*
#9	*			*
#10	*			*

Flaming debris no
 Non-flaming debris yes

*: afterflame time ≤ 2 s
 > 2 s: afterflame time > 2 s and ≤ 5 s
 > 5 s: afterflame time > 5 s

Reference: T2222496 - 3019 - col. 110
 T2222497 - 3019 - col. 994
 T2222498 - 3019 - col. 736

Classification of materials according to their reaction to fire - "Test for melting materials"

Date of ending the test 05-12-2022
 Standard used NF P92-505 (1995)
 Product standard NF P92-507 (2004)

Deviation from the standard A limited number of specimens have been tested for each sample.

Dimension of the specimens 70 mm x 70 mm x 2 mm
 Number of layers 5
 Weight (g/m²) T2222496:91
 T2222497:91
 T2222498:92

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure

Conditioning 23°C, relative humidity 50%
 Minimum 7 days or until constant mass is achieved

T2222496


		First ignition (s)	Non-flaming debris	Flaming debris	Ignition cotton wool	Mass (g)
#1	face A	*	yes	no	no	2.4
#2	face B	*	yes	no	no	2.4
#3						
#4						

* no ignition

T2222497

		First ignition (s)	Non-flaming debris	Flaming debris	Ignition cotton wool	Mass (g)
#1	face A	*	yes	no	no	2.5
#2	face B	*	yes	no	no	2.4
#3						
#4						

* no ignition



T2222498

		First ignition (s)	Non-flaming debris	Flaming debris	Ignition cotton wool	Mass (g)
#1	face A	*	yes	no	no	2.4
#2	face B	*	yes	no	no	2.4
#3						
#4						

* no ignition