



# CERTIFICATE

## **CENTEXBEL TYPE TESTING | TEST REPORT N° 22.06073.03**

According to report N° 22.06073.03, dated on 8/12/2022, we confirm that the below mentioned items were tested at CENTEXBEL with reference to **NF P 92-507 (2004) "Fire safety - Building - Interior fitting materials - Classification according to their reaction to fire"**.

The items show

## **Classification M1**

When properly applied.

The evaluation of the burning behaviour is based on CENTEXBEL's evaluation scheme.

### **SAMPLES**

3020

Various colours

### **Company**

ADO Goldkante GmbH & Co. KG

Zimmersmühlenweg 14-18

61440 OBERURSEL - GERMANY

This Certificate is valid until 8/12/2027

Centexbel | Technologiepark 70 | BE 9052 Gent | Belgium, 8/12/2022

Stijn Devaere, PhD  
Director Services



**ADO Goldkante GmbH & Co. KG**  
**Zimmersmühlenweg 14-18**  
**61440 OBERURSEL**  
**Germany**

**Your notice of**  
 15-11-2022

**Your reference**

**Date**  
 08-12-2022

## Analysis Report 22.06073.03

Required tests :

**NF P92-507 (2004)**

Sample id	Information given by the client	Date of receipt
T2223182	3020 - col. 110	23-11-2022
T2223183	3020 - col. 994	23-11-2022
T2223184	3020 - col. 543	23-11-2022



**Gina Créelle**  
**Order responsible**

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.  
 The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.  
 In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.



**Reference:** T2223182 - 3020 - col. 110  
 T2223183 - 3020 - col. 994  
 T2223184 - 3020 - col. 543

**Classification of materials according to their reaction to fire - "Electric burner"**

Date of ending the test 06-12-2022  
 Standard used NF P92-503 (1995)  
 Product standard NF P92-507 (2004)

Deviation from the standard A limited number of specimens have been tested for each sample.

Dimension of the specimens 600 mm x 180 mm x < 1 mm  
 Weight (g/m<sup>2</sup>)  
 T2223182: 46  
 T2223183: 46  
 T2223184: 47

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure

Conditioning 23°C, relative humidity 50%  
 Minimum 7 days or until constant mass is achieved

T2223182

	Length		Width	
	Face A	Face B	Face A	Face B
Hole formation	yes			yes
Max. afterflame time (s)	0	-	-	0
Afterglow	no			no
Afterglow with propagation in area > 25 cm	no			no
Damaged length (cm)	20.0	-	-	16.0
Damaged width (cm) in area >45 cm	0	-	-	0
Flaming molten droplets	no			no
Non-flaming molten droplets	no			no
Flaming debris	no			no
Non-flaming debris	no			no

### T2223183

	Length		Width	
	Face A	Face B	Face A	Face B
Hole formation		yes	yes	
Max. afterflame time (s)	-	0	0	-
Afterglow		no	no	
Afterglow with propagation in area > 25 cm		no	no	
Damaged length (cm)	-	20.5	21.5	-
Damaged width (cm) in area >45 cm	-	0	0	-
Flaming molten droplets		no	no	
Non-flaming molten droplets		no	no	
Flaming debris		no	no	
Non-flaming debris		no	no	

### T2223184

	Length		Width	
	Face A	Face B	Face A	Face B
Hole formation	yes			yes
Max. afterflame time (s)	0	-	-	0
Afterglow	no			no
Afterglow with propagation in area > 25 cm	no			no
Damaged length (cm)	22.0	-	-	20.0
Damaged width (cm) in area >45 cm	0	-	-	0
Flaming molten droplets	no			no
Non-flaming molten droplets	no			no
Flaming debris	no			no
Non-flaming debris	no			no



**Reference:** T2223182 - 3020 - col. 110  
 T2223183 - 3020 - col. 994  
 T2223184 - 3020 - col. 543

**Classification of materials according to their reaction to fire - "Flame persistence test"**

Date of ending the test	06-12-2022
Standard used	NF P92-504 (1995)
Product standard	NF P92-507 (2004)
Deviation from the standard	A limited number of specimens have been tested for each sample.
Dimension of the specimens	460 mm x 230 mm x < 1 mm
Weight (g/m <sup>2</sup> )	T2223182: 46 T2223183: 46 T2223184: 47

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure

Conditioning 23°C, relative humidity 50%  
 Minimum 7 days or until constant mass is achieved

Each test has been carried out with a flame application time of 5s.

### T2223182

	Length		Width	
	Face A	Face B	Face A	Face B
#1	*			*
#2	*			*
#3	*			*
#4	*			*
#5	*			*
#6	*			*
#7	*			*
#8	*			*
#9	*			*
#10	*			*

Flaming debris no  
 Non-flaming debris no

\*: afterflame time  $\leq 2$  s  
 > 2 s: afterflame time > 2 s and  $\leq 5$  s  
 > 5 s: afterflame time > 5 s

### T2223183

	Length		Width	
	Face A	Face B	Face A	Face B
#1		*	*	
#2		*	*	
#3		*	*	
#4		*	*	
#5		*	*	
#6		*	*	
#7		*	*	
#8		*	*	
#9		*	*	
#10		*	*	

Flaming debris no  
 Non-flaming debris no

\*: afterflame time  $\leq 2$  s  
 > 2 s: afterflame time > 2 s and  $\leq 5$  s  
 > 5 s: afterflame time > 5 s

	Length		Width	
	Face A	Face B	Face A	Face B
#1	*			*
#2	*			*
#3	*			*
#4	*			*
#5	*			*
#6	*			*
#7	*			*
#8	*			*
#9	*			*
#10	*			*

```

*: afterflame time  $\leq 2$  s
> 2 s: afterflame time  $> 2$  s and  $\leq 5$  s
> 5 s: afterflame time  $> 5$  s

```



**Reference:** T2223182 - 3020 - col. 110  
 T2223183 - 3020 - col. 994  
 T2223184 - 3020 - col. 543

**Classification of materials according to their reaction to fire - "Test for melting materials"**

Date of ending the test 07-12-2022  
 Standard used NF P92-505 (1995)  
 Product standard NF P92-507 (2004)

Deviation from the standard A limited number of specimens have been tested for each sample.

Dimension of the specimens 70 mm x 70 mm x 2 mm  
 Number of layers 9  
 Weight (g/m<sup>2</sup>) T2223182: 46  
 T2223183: 46  
 T2223184: 47

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure

Conditioning 23°C, relative humidity 50%  
 Minimum 7 days or until constant mass is achieved

**T2223182**

		First ignition (s)	Non-flaming debris	Flaming debris	Ignition cotton wool	Mass (g)
#1	face A	*	yes	no	no	2.2
#2	face B	*	yes	no	no	2.2
#3						
#4						

\* no ignition

**T2223183**

		First ignition (s)	Non-flaming debris	Flaming debris	Ignition cotton wool	Mass (g)
#1	face A	*	yes	no	no	2.2
#2	face B	*	yes	no	no	2.2
#3						
#4						

\* no ignition





T2223184

		First ignition (s)	Non-flaming debris	Flaming debris	Ignition cotton wool	Mass (g)
#1	face A	*	yes	no	no	2.2
#2	face B	*	yes	no	no	2.2
#3						
#4						

\* no ignition