

**For the Account of**

Zimmer & Rohde Germany  
Zimmersmuhlenweg 14-18  
61440 Oberursel  
Germany

**Client's Identification**

Reflekt FR RE

**CERTIFICATE OF TESTING****TEST PERFORMED** NFPA 701 Standard Methods of Fire Test for Flame Propagation of Textiles and Films 2023 – Test #1**TEST RESULTS**

Specimen	Mass Initial (g)	Mass Final (g)	Mass Loss (%)	Drip Burn (s)	Afterflame (s)
1	5.7	3.5	39	0.0	0.0
2	5.6	3.5	38	0.0	0.0
3	5.7	4.1	28	0.0	0.0
4	5.7	4.0	30	0.0	0.0
5	5.7	3.9	32	0.0	0.0
6	5.7	3.9	32	0.0	0.0
7	5.7	3.5	39	0.0	0.0
8	5.5	3.8	31	0.0	0.0
9	5.7	4.2	26	0.0	0.0
10	5.7	3.9	32	0.0	0.0
Average	5.7	3.8	33	0.0	0.0

**NOTES**

Approximate weight (oz./sq. yd) 2.8

Standard Deviation 4.5

Mean + 3 SD 46.5

Product Configuration  Single Layer  Multi Layer

Material Tested Initially

Test Environment 70 ±4°F, 50 ±5% Relative Humidity

Conditioning  Oven at 220°F (30 minutes)  70 ±4°F & 65 ±5%RH for 24 hours

Sampling As Received

Intended End-use Drapery

**ACCEPTANCE CRITERIA***Afterflame is required to be recorded; however, it is not factored into the Acceptance Criteria*

1. Drip burn (Flaming Drip) shall not exceed an average of 2 seconds per specimen for the sample of 10 specimens
2. Mass Loss shall not exceed 40% for the average of 10 specimens
3. Individual specimen mass loss shall not exceeds mean + 3 SD

**CONCLUSION** Based on the above Results and Acceptance Criteria, the item tested:

Complies  
 Does Not Comply  
 Testing of 10 additional specimens is required

**CERTIFICATION** I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

Authorized Signature

Date Order Completed: 11/19/2025