

For the Account of

Zimmer & Rohde Germany
Zimmersmuhlenweg 14-18
61440 Oberursel
Germany

Client's Identification

Linto Joy FR

CERTIFICATE OF TESTING

TEST PERFORMED NFPA 701 Standard Methods of Fire Test for Flame Propagation of Textiles and Films 2023 – Test #1

TEST RESULTS

Specimen	Mass Initial (g)	Mass Final (g)	Mass Loss (%)	Drip Burn (s)	Afterflame (s)
1	5.7	4.5	21	0.0	0.0
2	5.7	3.7	35	0.0	0.0
3	5.7	4.4	23	0.0	0.0
4	5.7	4.1	28	0.0	0.0
5	5.7	4.1	28	0.0	0.0
6	5.7	4.4	23	0.0	0.0
7	5.7	5.5	4	0.0	0.0
8	5.7	4.2	26	0.0	0.0
9	5.7	4.1	28	0.0	0.0
10	5.7	4.6	19	0.0	0.0
Average	5.7	4.4	24	0.0	0.0

NOTES

Approximate weight (oz./sq. yd) 2.8

Standard Deviation 8.2

Mean + 3 SD 48.6

Product Configuration

☒ Single Layer ☐ Multi Layer

Material Tested

Initially

Test Environment

70 ±4°F, 50 ±5% Relative Humidity

Conditioning

☒ Oven at 220°F (30 minutes) ☐ 70 ±4°F & 65 ±5%RH for 24 hours

Sampling

As Received

Intended End-use

Drapery

ACCEPTANCE CRITERIA

Afterflame is required to be recorded; however, it is not factored into the Acceptance Criteria

1. Drip burn (Flaming Drip) shall not exceed an average of 2 seconds per specimen for the sample of 10 specimens
2. Mass Loss shall not exceed 40% for the average of 10 specimens
3. Individual specimen mass loss shall not exceeds mean + 3 SD

CONCLUSION

Based on the above Results and Acceptance Criteria, the item tested:

- ☒ Complies
☐ Does Not Comply
☐ Testing of 10 additional specimens is required

CERTIFICATION I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.



Authorized Signature

Date Order Completed: 05/21/2026