

For the Account Of: Ado Goldkante GmbH & Co. KG
Zimmersmuhlenweg 14-18
61440 Oberursel
Germany

Client's Identification: 3123

CERTIFICATE OF TESTING

TEST PERFORMED *EN 13773:2003 Textiles and textile products-Burning behaviour-Curtains and drapes-Determination of the ignitability of vertically oriented specimens.*

TEST RESULTS

Length:

Flame Application time (s)	Cases of ignition	Cases of non-ignition
1	0	1
2	0	1
3	0	1
4	0	1
5	0	1
10	0	1
15	0	1
20	0	5

The mean of recorded times at which ignition was observed calculated: No Ignition within 20 s

Width:

Flame Application time (s)	Cases of ignition	Cases of non-ignition
1	0	1
2	0	1
3	0	1
4	0	1
5	0	1
10	0	1
15	0	1
20	0	5

The mean of recorded times at which ignition was observed calculated: No Ignition within 20 s

Length:

	Face A	Face B	Face A	Face A
Severance 1 st thread	No	No	No	No
Severance 2 nd thread	No	No	No	No
Severance 3 rd thread	No	No	No	No
Time to sever 3 rd thread (s)	/	/	/	/
Destroyed Length (mm)	120	125	130	155
Flaming debris	No	No	No	No

Width:

	Face A	Face B	Face A	Face A
Severance 1 st thread	No	No	No	No
Severance 2 nd thread	No	No	No	No
Severance 3 rd thread	No	No	No	No
Time to sever 3 rd thread (s)	/	/	/	/
Destroyed Length (mm)	130	130	130	135
Flaming debris	No	No	No	No

NOTES

Conditioning
Ignition
Sample Prep

20°C, Relative Humidity 65%
Bottom Edge
Tested as received

CONCLUSION

Classification in accordance with EN 13773

Class 1

CERTIFICATION I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.



Andrew Crowley
Quality Manager
Authorized Signature



Jillian Mattice
Account Manager
Verification Signature

Date Order Completed: 09/14/2021