



# CERTIFICATE

## **CENTEXBEL TYPE TESTING | TEST REPORT N° 21.05892.03**

According to report N° 21.05892.03, dated on 22/10/2021, we confirm that the below mentioned items were tested at CENTEXBEL with reference to **NF P 92-507 (2004) "Fire safety - Building - Interior fitting materials - Classification according to their reaction to fire"**.

The items show

## **Classification M1**

When properly applied.

The evaluation of the burning behaviour is based on CENTEXBEL's evaluation scheme.

### **SAMPLES**

3609

Various colours

### **Company**

Ado Goldkante GmbH Co Kg  
Zimmersmühlenweg 14-18  
61440 OBERURSEL - GERMANY

This Certificate is valid until 22/10/2026

Centexbel | Technologiepark 70 | BE 9052 Gent | Belgium, 22/10/2021

Stijn Devaere, PhD  
Director Services



**Ado Goldkante GmbH Co Kg**  
**Zimmersmühlenweg 14-18**  
**61440 OBERURSEL**  
**Germany**

**Your notice of**  
 21-09-2021

**Your reference**  
 3564694

**Date**  
 22-10-2021

## Analysis Report 21.05892.03

Required tests :

**NF P92-507 (2004)**

Sample id	Information given by the client	Date of receipt
T2120144	3609-111	21-09-2021
T2120145	3609-554	21-09-2021
T2120146	3609-685	21-09-2021



Gina Créelle  
 Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.  
 The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.  
 In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.



**Reference:** T2120144 - 3609-111  
T2120145 - 3609-554  
T2120146 - 3609-685

**Classification of materials according to their reaction to fire - "Electric burner"**

Date of ending the test 08-10-2021  
Standard used NF P92-503 (1995)  
Product standard NF P92-507 (2004)

Deviation from the standard A limited number of specimens have been tested for each sample.

Dimension of the specimens 600 mm x 180 mm x < 1 mm

Weight (g/m<sup>2</sup>)

T2120144	65
T2120145	67
T2120146	68

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure

Conditioning 23°C, relative humidity 50%  
Minimum 7 days or until constant mass is achieved

T2120144

	Length		Width	
	Face A	Face B	Face A	Face B
Hole formation	yes			yes
Max. afterflame time (s)	0	-	-	0
Afterglow	no			no
Afterglow with propagation in area > 25 cm	no			no
Damaged length (cm)	20.0	-	-	19.5
Damaged width (cm) in area >45 cm	0	-	-	0
Flaming molten droplets	no			no
Non-flaming molten droplets	no			no
Flaming debris	no			no
Non-flaming debris	no			no

#### T2120145

	Length		Width	
	Face A	Face B	Face A	Face B
Hole formation		yes	yes	
Max. afterflame time (s)	-	0	0	-
Afterglow		no	no	
Afterglow with propagation in area > 25 cm		no	no	
Damaged length (cm)	-	17.0	19.0	-
Damaged width (cm) in area >45 cm	-	0	0	-
Flaming molten droplets		no	no	
Non-flaming molten droplets		no	no	
Flaming debris		no	no	
Non-flaming debris		no	no	

#### T2120146

	Length		Width	
	Face A	Face B	Face A	Face B
Hole formation	yes			yes
Max. afterflame time (s)	0	-	-	0
Afterglow	no			no
Afterglow with propagation in area > 25 cm	no			no
Damaged length (cm)	20.5	-	-	18.5
Damaged width (cm) in area >45 cm	0	-	-	0
Flaming molten droplets	no			no
Non-flaming molten droplets	no			no
Flaming debris	no			no
Non-flaming debris	no			no



**Reference:** T2120144 - 3609-111  
 T2120145 - 3609-554  
 T2120146 - 3609-685

**Classification of materials according to their reaction to fire - "Flame persistence test"**

Date of ending the test	11-10-2021
Standard used	NF P92-504 (1995)
Product standard	NF P92-507 (2004)
Deviation from the standard	A limited number of specimens have been tested for each sample.
Dimension of the specimens	460 mm x 230 mm x < 1 mm
Weight (g/m <sup>2</sup> )	
T2120144	65
T2120145	67
T2120146	68

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure

Conditioning 23°C, relative humidity 50%  
 Minimum 7 days or until constant mass is achieved

Each test has been carried out with a flame application time of 5s.



#### T2120144

	Length		Width	
	Face A	Face B	Face A	Face B
#1	*			*
#2	*			*
#3	*			*
#4	*			*
#5	*			*
#6	*			*
#7	*			*
#8	*			*
#9	*			*
#10	*			*

Flaming debris no  
 Non-flaming debris yes

\*: afterflame time  $\leq 2$  s  
 > 2 s: afterflame time > 2 s and  $\leq 5$  s  
 > 5 s: afterflame time > 5 s

#### T2120145

	Length		Width	
	Face A	Face B	Face A	Face B
#1		*	*	
#2		*	*	
#3		*	*	
#4		*	*	
#5		*	*	
#6		*	*	
#7		*	*	
#8		*	*	
#9		*	*	
#10		*	*	

Flaming debris no  
 Non-flaming debris no

\*: afterflame time  $\leq 2$  s  
 > 2 s: afterflame time > 2 s and  $\leq 5$  s  
 > 5 s: afterflame time > 5 s



T2120146

	Length		Width	
	Face A	Face B	Face A	Face B
#1	*			*
#2	*			*
#3	*			*
#4	*			*
#5	*			*
#6	*			*
#7	*			*
#8	*			*
#9	*			*
#10	*			*

Flaming debris no  
 Non-flaming debris no

\*: afterflame time  $\leq 2$  s  
 > 2 s: afterflame time > 2 s and  $\leq 5$  s  
 > 5 s: afterflame time > 5 s



**Reference:** T2120144 - 3609-111  
 T2120145 - 3609-554  
 T2120146 - 3609-685

**Classification of materials according to their reaction to fire - "Test for melting materials"**

Date of ending the test 21-10-2021  
 Standard used NF P92-505 (1995)  
 Product standard NF P92-507 (2004)

Deviation from the standard A limited number of specimens have been tested for each sample.

Dimension of the specimens 70 mm x 70 mm x < 1 mm  
 Number of layers 6  
 Weight (g/m<sup>2</sup>)  
 T2120144 65  
 T2120145 67  
 T2120146 68

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure

Conditioning 23°C, relative humidity 50%  
 Minimum 7 days or until constant mass is achieved

Four specimens, two on both sides, have been tested .

T2120144

		First ignition (s)	Non-flaming debris	Flaming debris	Ignition cotton wool	Mass (g)
#1	face A	*	yes	no	no	2.1
#2	face B	*	yes	no	no	2.1
#3	face A					
#4	face B					

\* no ignition





#### T2120145

		First ignition (s)	Non-flaming debris	Flaming debris	Ignition cotton wool	Mass (g)
#1	face A	*	yes	no	no	2.1
#2	face B	*	yes	no	no	2.1
#3	face A					
#4	face B					

\* no ignition

#### T2120146

		First ignition (s)	Non-flaming debris	Flaming debris	Ignition cotton wool	Mass (g)
#1	face A	*	yes	no	no	2.1
#2	face B	*	yes	no	no	2.1
#3	face A					
#4	face B					

\* no ignition