



## Test Report

No.: SL119002782611TX

Date: Aug 13, 2019

Page 1 of 2

ZIMMER & ROHDE GMBH  
ZIMMERSMUHLENWEG  
14-18 OBERURSER  
FRANKFURT, 61440, GERMANY

The following sample was submitted and identified by the client as:

ONE SAMPLE OF WOVEN 44162 FABRIC

Item No.	:	44162
Country Of Destination	:	HK/ ASIA/ ME / INTERNATIONAL
Sample Receiving Date	:	Aug 07, 2019
Test Performing Period	:	Aug 07, 2019 – Aug 13, 2019
Test Performed	:	Selected test(s) as requested by applicant against specified requirement (details please refer to result page(s)).

\* \* \* \*

Test Results : Please refer to the next page(s).

Conclusions : Abrasion Resistance

F

Remarks : F = Below specified requirement

Signed for and on behalf of  
SGS Hong Kong Ltd.

Chan Kai Kong Alfred  
Assistant Technical Manager

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.





## Test Report

No.: SL119002782611TX

Date: Aug 13, 2019

Page 2 of 2

### Test Results :

#### Abrasion Resistance

(DIN EN ISO 12947-2(2017-03); Martindale Wear & Abrasion Tester ; 9 kPa Pressure)

End point (rubs)  
Average

33700

#### Specified Requirement

Exceed 55000

\*\*\*\*\* End of Report \*\*\*\*\*

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.