

ZIMMER & ROHDE GMBH
ZIMMERSMUEHLENWEG 14-18, OBERURSEL, 61440, Germany

The following sample(s) was/were submitted and identified on behalf of the client as:

Sample Description : One sample of woven cutting.

Item No. : 44202

Country of Destination : HK/ ASIA/ ME / INTERNATIONAL

Sample Receiving Date : Jul 07, 2022

Testing Period : Jul 07, 2022 - Jul 18, 2022

Test Result(s) : Unless otherwise stated the results shown in this test report refer only to the sample(s) tested, for further details, please refer to the following page(s).

Test Performed : Selected test(s) as requested by applicant

Signed for and on behalf of
SGS (Hong Kong) Limited



Chan Kai Kong, Alfred, Technical Manager

Test Result

Abrasion Resistance

(DIN EN ISO 12947-2:2017; Martindale Abrasion & Pilling Tester, Pressure: 9kPa)

As Received

-	Unit	A	Requirement
The quoted result	Rubs	Exceed 100,000 rubs	-

Sample Photo



***** End of Report *****

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.