

Confidential Report

Our Ref: 23/61627D1/12/23







Telephone: +44 (0) 113 259 1999 Email: onestopshop@bttg.co.uk

Website: www.bttg.co.uk

Date: 11 December 2023

Our Ref: 23/61627D1/12/23

Your Ref:

Page: 1 of 4

Client: Zimmer + Rohde GmbH

Zimmersmuhlenweg 14-18 61440 Oberursel Frankfurt Germany

Job Title: Fire Test on One Fabric Sample

Clients Order Ref: --

Date of Receipt: 05 December 2023

Date Test Started: 11 December 2023

Description of Sample: One sample of fabric, which was referenced by the client as;

44214, 30% LI, 30% CO, 18% WO, 12% CV, 10% PES

Work Requested: We were asked to make the following fire test:

BS EN 1021:Part 1:2014 – Ignitability of Upholstered Furniture

- * subcontracted test, UKAS accredited
- subcontracted test, EN ISO/IEC 17025 accredited
- *** not UKAS accredited





Note: This report relates only to the items tested.



Telephone: +44 (0) 113 259 1999 Email: onestopshop@bttg.co.uk Website: www.bttg.co.uk

11 December 2023

Our Ref: 23/61627D1/12/23

Date:

Your Ref: ---

Page: 2 of 4

Client: Zimmer + Rohde GmbH

FIRE TESTS ACCORDING TO BS EN 1021-1:2014

Assessment of the ignitability of upholstered furniture. Part 1. Ignition Source 1: Smouldering cigarette.

Pre-Treatment

The material received no pre-treatment as the fabric is stated not to be FR treated.

Conditioning

The materials for testing to Source 0 and 1 were conditioned for a minimum of 24 hours and tested in the environments specified in Clause 7 of BS EN 1021-1 & 2:2014.

The sample was tested in a room of volume 25m³ and 17°C.

Procedure

The test was carried out in accordance with BS EN 1021-2:2014. The sponsor sampled the material and the specimens were cut from the sample received to the dimensions set out in the standard.

The sample was tested over non-fire retardant polyurethane foam with a density of approximately 20-22 kg/m³.

Tests were made using ignition source 1.

Requirements

The specimens shall not:-

Smouldering Criteria

- a) display escalating combustion requiring active extinction.
- b) smoulders until it is essentially consumed within the test duration.
- c) smoulder to the extremities of the specimen, or through the full thickness, within the duration of the test.
- d) smoulder for more than one hour.
- e) show evidence of charring, other than discolouration, for more than 100mm in any direction apart from the nearest part of the original position of the source.







Telephone: +44 (0) 113 259 1999 Email: onestopshop@bttg.co.uk

Website: www.bttg.co.uk

11 December 2023 Date:

Our Ref: 23/61627D1/12/23 Your Ref:

> Page: 3 of 4

Client: Zimmer + Rohde GmbH

Requirements (Continued)

Flaming Criteria

show evidence of flaming initiated by a smouldering source. a)

Results

	Specimen No.		
Smouldering criteria	1	2	3 ¹
Unsafe escalating combustion	No	No	
Testing assembly consumed	No	No	
Smoulders to extremities/full thickness	No	No	
Smoulders more than 1 hour	No	No	
In final examination, presence of progressive	No	No	
smouldering			

Flaming criteria	1	2	31
Occurrence of flames	No	No	
Specimen Result Ignition (I) / Non Ignition (NI)	NI	NI	

Note

The test results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.







Telephone: +44 (0) 113 259 1999 Email: onestopshop@bttg.co.uk

Website: www.bttg.co.uk

11 December 2023 Date:

Our Ref: 23/61627D1/12/23

Your Ref:

Page: 4 of 4

Zimmer + Rohde GmbH Client:

Comment

An NI designation indicates that the sample meets the performance requirements of BS EN 1021-1.

Where required to make a judgement to any pass/fail criteria an estimation of uncertainty of measurement has been taken into account. Under our Policy we have used a non-binary decision rule.

See our decision rules Policy (https://www.bttg.co.uk/about-us/decision-rules-policy/) for further information.

Uncertainty Budget

The overall uncertainty budget for BS EN 1021: Part 1:2014 is as follows:-

Timings: ±2 seconds. Measurements: ±2mm.

Reported by:..... R Greasley, Laboratory Technician

..... B Bland, Technical Customer Service Officer Countersigned by:.....

Enquiries concerning this report should be addressed to Customer Services.



