



# CERTIFICATE

## CENTEXBEL TYPE TESTING | TEST REPORT N° 23.05804.06

According to report N° 23.05804.06, dated on 19/12/2023, we confirm that the below mentioned items were tested at CENTEXBEL with reference to **NF P 92-507 (2004) "Fire safety - Building - Interior fitting materials - Classification according to their reaction to fire"**.

The item shows

## Classification M1

Provided that it is properly applied.

The evaluation of the burning behaviour is based on CENTEXBEL's evaluation scheme.

### SAMPLES

**6000**

Various colours

### Company

Ado Goldkante GmbH & Co. Kg  
Zimmersmühlenweg 14-18  
61440 OBERURSEL  
GERMANY

This Certificate is valid until 19/12/2028

Centexbel | Technologiepark 70 | BE 9052 Gent | Belgium, 19/12/2023

Jan Laperre  
General Manager

A blue ink handwritten signature of Jan Laperre, consisting of a large loop and a vertical stroke.



**ADO Goldkante GmbH & Co. KG**  
**Zimmersmühlenweg 14-18**  
**61440 OBERURSEL**  
**Germany**

**Your notice of**  
27-10-2023

**Your reference**

**Date**  
19-12-2023

## Analysis Report 23.05804.06

Required tests :

**NF P92-507 (2004)**

Sample id	Information given by the client	Date of receipt
T2327566	6000-558	06-12-2023
T2327567	6000-131	06-12-2023
T2327568	6000-998	06-12-2023

Gina Créelle  
Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.  
The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.  
In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.

Samples

T2327566  
6000-558



T2327567  
6000-131



T2327568  
6000-998



INRICHTING ERKENDE BIJ TOEPASSING VAN DE BESLUITWET VAN 30 JANUARI 1947 / ETABLISSEMENT RECONNU PAR APPLICATION DE L'ARRÊTE-LOI DU 30 JANVIER 1947

**Reference:** T2327566 - 6000-558  
T2327567 - 6000-131  
T2327568 - 6000-998

**Classification of materials according to their reaction to fire - "Electric burner"**

Date of ending the test 18-12-2023  
Standard used NF P92-503 (1995)  
Product standard NF P92-507 (2004)

Deviation from the standard A limited number of specimens have been tested for each sample.

Dimension of the specimens 600 mm x 180 mm x < 1 mm  
Weight (g/m<sup>2</sup>)  
T2327566: 49  
T2327567: 49  
T2327568: 50

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure

Conditioning 23°C, relative humidity 50%  
Minimum 7 days or until constant mass is achieved

T2327566

	Length		Width	
	Face A	Face B	Face A	Face B
Hole formation	yes			yes
Max. afterflame time (s)	0	-	-	0
Afterglow	no			no
Afterglow with propagation in area > 25 cm	no			no
Damaged length (cm)	18.5	-	-	21.0
Damaged width (cm) in area >45 cm	0	-	-	0
Flaming molten droplets	no			no
Non-flaming molten droplets	no			no
Flaming debris	no			no
Non-flaming debris	no			no

T2327567

	Length		Width	
	Face A	Face B	Face A	Face B
Hole formation		yes	yes	
Max. afterflame time (s)	-	0	0	-
Afterglow		no	no	
Afterglow with propagation in area > 25 cm		no	no	
Damaged length (cm)	-	21.5	19.0	-
Damaged width (cm) in area >45 cm	-	0	0	-
Flaming molten droplets		no	no	
Non-flaming molten droplets		no	no	
Flaming debris		no	no	
Non-flaming debris		no	no	

T2327568

	Length		Width	
	Face A	Face B	Face A	Face B
Hole formation	yes			yes
Max. afterflame time (s)	0	-	-	0
Afterglow	no			no
Afterglow with propagation in area > 25 cm	no			no
Damaged length (cm)	17.5	-	-	19.5
Damaged width (cm) in area >45 cm	0	-	-	0
Flaming molten droplets	no			no
Non-flaming molten droplets	no			no
Flaming debris	no			no
Non-flaming debris	no			no

**Reference:** T2327566 - 6000-558  
T2327567 - 6000-131  
T2327568 - 6000-998

**Classification of materials according to their reaction to fire - "Flame persistence test"**

Date of ending the test	19-12-2023
Standard used	NF P92-504 (1995)
Product standard	NF P92-507 (2004)
Deviation from the standard	A limited number of specimens have been tested for each sample.
Dimension of the specimens	460 mm x 230 mm x < 1 mm
Weight (g/m <sup>2</sup> )	T2327566: 49 T2327567: 49 T2327568: 50

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure

Conditioning 23°C, relative humidity 50%  
Minimum 7 days or until constant mass is achieved

Each test has been carried out with a flame application time of 5s.

T2327566

	Length		Width	
	Face A	Face B	Face A	Face B
#1	*			*
#2	*			*
#3	*			*
#4	*			*
#5	*			*
#6	*			*
#7	*			*
#8	*			*
#9	*			*
#10	*			*

Flaming debris                                  no  
Non-flaming debris                              yes

\*: afterflame time  $\leq 2$  s  
 $> 2$  s: afterflame time  $> 2$  s and  $\leq 5$  s  
 $> 5$  s: afterflame time  $> 5$  s

T2327567

	Length		Width	
	Face A	Face B	Face A	Face B
#1		*	*	
#2		*	*	
#3		*	*	
#4		*	*	
#5		*	*	
#6		*	*	
#7		*	*	
#8		*	*	
#9		*	*	
#10		*	*	

Flaming debris                                  no  
Non-flaming debris                              no

\*: afterflame time  $\leq 2$  s  
 $> 2$  s: afterflame time  $> 2$  s and  $\leq 5$  s  
 $> 5$  s: afterflame time  $> 5$  s





**Reference:** T2327566 - 6000-558  
T2327567 - 6000-131  
T2327568 - 6000-998

**Classification of materials according to their reaction to fire - "Test for melting materials"**

Date of ending the test 19-12-2023  
Standard used NF P92-505 (1995)  
Product standard NF P92-507 (2004)

Deviation from the standard A limited number of specimens have been tested for each sample.

Dimension of the specimens 70 mm x 70 mm x 1 mm  
Number of layers  
Weight (g/m<sup>2</sup>) T2327566: 49  
T2327567: 49  
T2327568: 50

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure

Conditioning 23°C, relative humidity 50%  
Minimum 7 days or until constant mass is achieved

T2327566


		First ignition (s)	Non-flaming debris	Flaming debris	Ignition cotton wool	Mass (g)
#1	face A	*	yes	no	no	2.2
#2	face B	*	yes	no	no	2.2
#3						
#4						

\* no ignition

T2327567

		First ignition (s)	Non-flaming debris	Flaming debris	Ignition cotton wool	Mass (g)
#1	face A	*	yes	no	no	2.1
#2	face B	*	yes	no	no	2.1
#3						
#4						

\* no ignition



T2327568

		First ignition (s)	Non-flaming debris	Flaming debris	Ignition cotton wool	Mass (g)
#1	face A	*	yes	no	no	2.1
#2	face B	*	yes	no	no	2.2
#3						
#4						

\* no ignition